

UNCLASSIFIED

AD NUMBER

AD058544

CLASSIFICATION CHANGES

TO: **UNCLASSIFIED**

FROM: **CONFIDENTIAL**

LIMITATION CHANGES

TO:

**Approved for public release; distribution is
unlimited.**

FROM:

**Distribution authorized to U.S. Gov't. agencies
and their contractors;
Administrative/Operational Use; 10 MAR 1955.
Other requests shall be referred to Bureau of
Ordnance, Department of the Navy, Washington,
DC 20350.**

AUTHORITY

**31 Mar 1967, DoDD 5200.10; USNSWC notice dtd 12
Feb 1980**

THIS PAGE IS UNCLASSIFIED

AD-058544

USADACS Technical Library

5 0712 01014171 0

CONFIDENTIAL

115718Z

NPG Report No. 1342

NAVORD REPORT NO. 1339

TECHNICAL
LIBRARY

C-5685

DEVELOPMENT AND TEST OF NYLON ROTATING BAND
FOR 20MM HIGH VELOCITY PROJECTILE

Regraded

Unclassified

By authority of DTIC (AD 58 544)

Date

8 June 81

EXCLUDED FROM GENERAL
DECLASSIFICATION SCHEDULE



U. S. NAVAL PROVING GROUND
DAHLGREN, VIRGINIA

Rotating Band

Copy No. 54

Date 10 March 1955

CONFIDENTIAL

DISCLAIMER NOTICE

**THIS DOCUMENT IS BEST QUALITY
PRACTICABLE. THE COPY FURNISHED
TO DTIC CONTAINED A SIGNIFICANT
NUMBER OF PAGES WHICH DO NOT
REPRODUCE LEGIBLY.**

~~CONFIDENTIAL~~

U. S. Naval Proving Ground
Dahlgren, Virginia

Development and Test of Nylon Rotating Band
for 20mm High Velocity Projectile

by

R. B. Butler
Terminal Ballistics Department

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Task Assignment No.
NPG-B-3b-225-1-54

10 March 1955

APPROVED: J. F. BYRNE
Captain, USN
Commander, Naval Proving Ground

E.A.Ruckner

E. A. RUCKNER
Captain, USN
Ordnance Officer
By direction

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

CONTENTS

	<u>Page</u>
Abstract	ii
Foreword	iii
Introduction	1
Procedure and Results.	1
Discussion	11
Conclusions.	13
References	13
Appendices:	
A. NPG Photographs and Drawings (Figures 1-15)	
B. Recovery Data (Tables 1-3)	
C. Velocity and Pressure-Time Data (Table 4 and Figures 16-18)	
D. Accuracy Data (Tables 5-7)	
E. Data Pertaining to the Rapid-Fire Gun Life Tests	
F. Rapid-Fire Data - Chrome Plated Guns (Tables 8-27)	
G. Rapid-Fire Data - Unplated Guns (Tables 28-37)	
H. Distribution	

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

ABSTRACT

Previously reported work on the development of a nylon rotating band for the 20mm aircraft gun Mk 12 had shown that the band as developed imparted full spin to the projectile, obturated satisfactorily, and did not fringe noticeably or produce unacceptable yaw, in slow fire at muzzle velocities up to 3500 ft/sec and at temperatures from -65° to 160°F. On the basis of a relatively small amount of firing, the band appeared to be completely retained in flight even at the temperature extremes. This report continues the account of the development work on this band, including additional extreme temperature firing, firing for ballistic accuracy, and rapid-fire tests.

The extreme temperature firing indicated that a band design and a method of molding have been achieved which produce a band that is retained in flight at all firing conditions.

The rapid fire results showed that very satisfactory performance of the band is obtained even in a very hot gun. In chromium-plated barrels the nylon bands produce a spectacular increase in gun life. One barrel has been fired for over 2400 rounds on a severe schedule with practically no wear, while a similar barrel fired on the same schedule with gilding-metal bands was worn out after 1000 rounds. Unplated barrels also show an increase in life with nylon bands, but not to a similar extent. No evidence of band loss in rapid fire has been observed. Yaw performance in rapid fire has been in some cases inferior to that observed with gilding-metal bands, but none of these cases having occurred at less than 150 rounds of burst firing, they are not considered to be of importance in service use. The short-range dispersion obtained in rapid fire is generally comparable with that obtained with gilding-metal bands.

In accuracy firing (slow fire in a Mann barrel) acceptable dispersion at long range is obtained.

A report bearing on the storage life of nylon bands is in preparation.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

FOREWORD

The work described in this report was conducted by authority of reference (a) under Task Assignment NPG-B-3b-225-1-54, during the period 1 February 1953 to 1 May 1954. This is the twentieth partial report submitted under this task assignment, "Projectile Rotating Bands and Components".

The nylon bands injection molded on the projectiles and fired in these tests were produced by Nylon Molded Products Corporation, Garrettsville, Ohio, (commercial molders) or by the Naval Ordnance Laboratory. The Naval Ordnance Laboratory molding was done under the technical supervision of S. Prosen of the Plastics Division. Chromium plating of Mk 11 gun barrels was accomplished at the National Bureau of Standards, under the technical supervision of J. Young.

The tests upon which this report is based were conducted by:

T. W. TRUSLOW, Lieutenant (jg), USN
Light Armor Firing Officer
Terminal Ballistics Department
J. J. KOPCHINSKI, Aviation Ordnance Department
R. B. BUTLER, Head, Design Branch
Terminal Ballistics Department

This report was reviewed by:

H. L. DeROCHER, Head, Engineering Division
Terminal Ballistics Department
W. B. ROBERTSON, Commander, USN
Terminal Ballistics Officer
R. H. LYDDANE, Assistant Director of Research
N. A. M. RIFFOLT, Director of Research

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

INTRODUCTION

Reference (b) reported the original design and development work on a nylon rotating band for the 20mm Mk 12 aircraft gun, as well as the results of the evaluation in slow fire of relatively small samples of band models for spin, obturation, fringing, yaw near the muzzle, degree of band retention in flight, and performance at extreme temperatures. It was found that the bands developed imparted full spin to the projectile, obturated satisfactorily, and did not fringe noticeably or produce unacceptable yaw, in slow fire from a Mk 12 gun at muzzle velocities up to 3500 ft/sec and at temperatures from -65° to 160°F. On the basis of a relatively small amount of firing, the bands appeared to be completely retained in flight even at the temperature extremes.

This report continues the account of the development work on this band, including more extreme temperature firing, accuracy firings, and rapid-fire tests.

PROCEDURE AND RESULTS

Recovery Firing to Determine Band Retention

The bands under evaluation in this phase were of two NOL lots, previous tests of which, as well as manufacturing details, were reported in reference (b). Briefly, the two lots were the same except that Lot 4A was molded at a mold temperature of 190°F and a projectile temperature of 160°F, while for Lot 4B the mold was at 60°F and the projectile at 75°F. Both lots were of 0.3 long bands, molded on Type 2 Mod 2 projectiles, as shown in Figure 1, left.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Projectiles from each lot were subjected to temperature conditioning as follows:

No. of Rounds

<u>Lot 4A</u>	<u>Lot 4B</u>	<u>Conditioning</u>
10	10	Dry at 160°F for 7 days, ambient for 24 hours, -65°F for 4 hours, fired at -65°F.
10	10	-65°F for 4 hours, +160°F (dry) for 4 hours, ambient for 16 hours, this cycle repeated 7 times. Projectiles brought to -65°F for 4 hours and fired.
7	10	160°F and 100% relative humidity for 7 days, fired at 160°F.

The projectiles were fired for recovery from a new Mk 11 Mod 2 barrel. Microflash photographs (Figure 2 shows typical examples) were taken of all rounds in flight at 100 feet from the muzzle and spin was determined for some of the rounds on each test. The results are shown in detail in Tables 1, 2, and 3 (Appendix B). Except for band retention in the case of the lot 4A projectiles fired at -65°F, both lots performed satisfactorily in every regard at both high and low temperature. Out of 20 projectiles from lot 4A fired at -65°F, six showed some band loss. Results of the initial test of these lots (reported in reference (b)) also indicated that lot 4A bands would not be uniformly retained when fired at -65°F. Counting both tests, a total of 83 rounds have been fired at high, low and ambient temperatures. At -65°F lot 4A showed incomplete band retention on 8 out of 25 projectiles fired. Eight projectiles at ambient and seven projectiles at +160°F showed no loss. On the other hand no loss for lot B was shown for 25 projectiles fired at -65°F, 8 at ambient and 10 at +160°F.

~~CONFIDENTIAL~~

Neither lot showed any detectable deterioration in performance after a week's temperature cycling, nor after a week's exposure to 160°F and 100% humidity, which produces a soft band by reason of temperature softening and softening by moisture absorption. It is interesting to observe, in view of the fears which have sometimes been expressed of rapid and excessive dimensional changes of FM 10001 nylon, either by thermal expansion or moisture absorption, that in a week's exposure to such extreme conditions these latter bands increased in diameter by about 0⁰004, which is not enough to cause any interference with the gun chamber.

In view of the better band retention of Lot 4B, all nylon-banded 20mm projectiles subsequently procured, except a few for mold temperature studies, have been molded under similar conditions of mold and projectile temperature.

Development of Special Crimp

An attempt was now made to fire a powder charge determination, preparatory to conducting standard rapid-fire tests to determine gun life and projectile performance with 0⁰3 long nylon bands. In the 15-round bursts, which are a part of the charge determination, and which were the first bursts fired with 20mm nylon-banded projectiles, numerous small pieces of nylon were observed to be emitted from the breech of the gun.

This caused alarm, and the phenomenon was investigated by making up 15-round belts of standard ammunition with all rounds live except the last, which had an inert powder charge and a nylon band. When the belt was burst-fired, the nylon-banded round came to rest in the chamber, after going through the normal loading cycle, and was extracted and examined. It was found that the nylon bands were chipping and losing pieces by reason of the forward motion of the case over the projectile upon impact of the belt mechanism on the base of the case. This forward motion is not a new phenomenon since it is commonly observed with

standard gilding-metal-banded rounds, but while the gilding-metal band is sufficiently strong to act as a stop for the case without damage to itself, the nylon band is not. One of the rounds loaded in the fashion described is shown after extraction in Figure 3, left. High-speed motion pictures of the loading process confirmed that the band damage was occurring in this manner.

It was thus necessary either to improve the strength of the crimp, or to provide a stop other than the band for the forward motion of the case. Several attempts to improve the crimp strength were made, involving a deeper crimping groove, a double groove, or a more favorably shaped groove, but none of these was fully successful. Crimping the case with its forward edge as far back of the band as practicable, so as to permit a maximum forward motion before the band was contacted, was also unsuccessful. The problem was finally solved by cutting a notch, between the standard crimping groove and the after edge of the band, to hold the mouth of the case and prevent its touching the band. The mouth of the case is forced into this notch by a special jig during the operation of assembling projectile and case. The round is then rubber-crimped in the standard manner. This procedure, as compared with the standard assembly, involves no additional trouble or expense other than the cost of the special jig, and has been in use on all nylon-banded rounds fired subsequent to its development, with only a few exceptions when slow fire tests were conducted. Figure 4 shows the contour of the notch, and Figure 3, right, shows a round with the modified crimping groove after loading and extraction.

The deformation of the case mouth into the notch has caused no appreciable case damage on firing in slow fire or in bursts.

Abandonment of the 0¹/2 Band

About the same time, burst firing in a standard-twist unplated barrel was attempted with bands 0¹/2 long, earlier work on which has been described in reference (b). Some doubts had previously been felt about the adequacy of this design, which were justified when on the burst firing the

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

majority failed badly to impart the required spin. In view of this result, the 0.72 band was abandoned, and no further work on it attempted. All projectiles fired subsequently have been of the Type 2 Mod 2 design, with bands 0.83 long and 0.828 in diameter (Figure 5), with the exception of some projectiles, as described later, with variations in diameter.

Determination of Pressure-Time Data

Pressure time data were obtained for nylon- and gilding-metal-banded projectiles fired from a Mann barrel fitted with a piezoelectric pressure gauge. Two different nylon bands were employed in this work, both 0.83 long, one 0.828 and the other 0.834 in diameter. The detailed results are given in Appendix C.

In brief, the results indicated little difference among the three types of projectile, except for a tendency for the nylon-banded projectiles to give a peak pressure one to two tons lower for about the same muzzle velocity and muzzle pressure. This is in line with what has been observed for nylon bands in other calibers, and is attributed to the lower engraving force and diminished bore friction characteristic of nylon.

Accuracy Tests

Three accuracy tests were fired from Mann barrels to determine the performance of the nylon-banded projectiles. In the first of these, six ten-round groups were fired at a vertical target 600' from the gun. One group consisted of reference rounds (standard gilding-metal-banded Mk 11 Mod 0 projectiles); one of Type 2 Mod 2 projectiles; one of Type 2 Mod 2 projectiles crimped in the case with the same crimp as the standard gilding-metal-banded projectiles, that is, without the additional crimping notch used with the other nylon-banded projectiles; one of Type 2 Mod 2 projectiles at -65°F; and one each of Type 2 projectiles at band diameters of 0.823 and 0.834. The projectiles with 0.834 bands were not crimped at all, since it was discovered too late that they could not be crimped without modifying the equipment.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

In the second test, 25 or 26-round groups were fired at 1500 yards range, comparing standard projectiles, Type 2 Mod 2 projectiles, and Type 2 projectiles with band diameter of 0".834 and 0".836 diameters.

In the third test, ten-round groups were fired at 600' range, comparing reference projectiles, Type 2 Mod 2 projectiles, and Type 2 Mod 6 projectiles, the latter being identical to the Type 2 Mod 2 projectiles except for the provision of an after bourrelet behind the band of 0".784 diameter (an increase in diameter of 0".014).

The detailed results are given in Appendix D, and are summarized in the following table, which gives for each group the horizontal and vertical standard deviations in mils, and the RMS average of these two quantities. If horizontal and vertical dispersions are equal, the RMS average gives the best estimate of a figure of merit for the accuracy of the round.

Standard Deviations (Mils) of Points of Impact of Nylon-banded 20mm Mk 11-0 Projectiles Fired from Accuracy Barrels

<u>Projectile Type</u>	<u>Horizontal</u>	<u>Vertical</u>	<u>RMS Average</u>
------------------------	-------------------	-----------------	--------------------

Test of 10-round groups at 600' range on 7 August 1953

Standard	0.40	0.20	0.31
T2-2	0.50	0.79	0.66
T2-2 (Service Crimp)	0.87	0.74	0.80
T2-2 (at -65°F)	0.52	0.35	0.44
T2 at 0".823 diameter	0.54	0.44	0.49
T2 at 0".834 diameter (Not crimped)	0.36	0.53	0.46

Test of 25-26-round groups at 1500 yd. range on 22-26 August 1953

Standard	0.41	0.40	0.40
T2-2	0.62	0.90	0.77
T2 at 0".834 diameter	0.57	0.63	0.60
T2 at 0".836 diameter	0.60	0.67	0.64

Test of 10-round groups at 600' range on 11 March 1954

Standard	0.34	0.21	0.28
T2-2	0.36	0.45	0.41
T2-6	0.77	0.66	0.72

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

These results show a general increase in standard deviation for nylon over gilding metal. For the Type 2 Mod 2 projectile this increase is by a factor of 1.5 to 2. Firing the nylon band cold (-65°F) or at large or small diameter appears to improve the accuracy somewhat, although it does not bring it up to the level of the gilding metal band. There was initially considerable doubt whether the greater dispersion with nylon was to be attributed to a less firm centering of the projectile in the gun, particularly at exit, or to a small amount of fringing. The diminished dispersion with cold bands and with bands of altered diameters could support either hypothesis. In an effort to distinguish, the Type 2 Mod 6 projectiles were made up and fired in the third test. That this projectile, with a larger body diameter aft of the band, showed greater dispersion is considered to support the idea that there is some degree of fringing which causes the increased dispersion.

The actual amount of dispersion for the nylon-banded projectile is not great, and it is considered that in service the increase over the metal-banded projectile would be completely masked by dispersion attributable to the gun, the fire control system, and the aircraft.

Rapid-Fire Tests

The standard firing cycle for rapid-fire barrel life tests with the 20mm Mk 12 gun consists of twelve 50-round bursts (fired at a rate of about 1000 rounds per minute), with two minutes between bursts, and with complete cooling following the end of the cycle (600 rounds). In some cases, cold erosion checks are also fired. The criteria for end of life of the barrel, arrived at from experience with gilding-metal bands, are a 200 ft/sec loss in velocity averaged over a 50-round burst, or occurrence of yaw greater than 15° on 20% or more of the rounds in a burst, whichever occurs first.

In the rapid-fire tests, velocity, yaw, and dispersion are measured, and star-gauging of the barrel is conducted. Details of these measurements, as well as data on the ammunition components and assembly, will be found in Appendix E.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Retention of nylon bands in rapid-fire was judged either by a thorough search of the ground in front of the gun for band fragments, or by firing through a wire-screen enclosure 30" x 30" x 48' long and checking for the presence of band fragments after each burst. No nylon band fragments were found in any test.

All nylon bands used in the rapid-fire tests were molded by Nylon Molded Products Corporation, and while all were molded under the same conditions so far as these could be controlled, the projectiles will be identified by lot numbers. A lot is defined as a set of projectiles whose bands have been molded in one mold, on one machine, and in the same run.

The barrels employed were either standard Mk 11 Mod 2 barrels (unplated), or Mk 11 Mod 2 barrels modified at the Bureau of Standards by electropolishing and plating chamber and bore with 0.006 of hard chromium.

The detailed data obtained in all the rapid-fire tests are contained in Appendices F (plated barrels) and G (unplated barrels). For convenience, the velocity data and barrel erosion results are summarized graphically in Figures 6 to 11, Appendix A, and the yaw and dispersion data are summarized in the table on the following page.

The first barrel tested with nylon bands was No. EX-184, a plated barrel. On the first two erosion cycles in this barrel, although gun wear was negligible, velocity maintenance excellent, and dispersion acceptable, a large number of yawed rounds were encountered.

With nylon bands, the first round in each burst in a well-heated gun, being charged into the chamber and remaining there for ten or fifteen seconds before firing, usually shows a large yaw. This is to be attributed to band failure as a result of heating the band, and it is not considered entirely fair to count this round in applying the yaw criterion stated above. The effect is of little service importance, since it does not occur until 150-200 rounds have been fired.

~~Confidential~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

SUMMARY OF YAW AND DISPERSION DATA

Barrel No.	Erosion Cycle	Band	Percentage of Rounds with Yaw in the Range				Measured Rds. in Cycle	Average Pattern Size for 50-round Burst (91' Muzzle Distance)	
			0-5°	6-10°	11-15°	Over 15°		Horizontal (ins.)	Vertical (ins.)
<u>Plated Barrels</u>									
EX-184	1	Nylon Lot S2A	40.6	16.2	18.2	24.9	598	598	22.4
	2	Nylon Lot S2B	43.5	18.0	21.1	17.4	596	596	20.8
	3	Nylon Lot S9	80.8	13.5	4.7	1.0	598	613	17.4
	4	Nylon Lot S10, S10M, S9	93.6	2.9	2.1	1.3	595	607	19.4
855108	1	Nylon Lot S10M	77.0	10.5	8.6	3.8	572	613	17.9
854254	1	Nylon Lot S9	86.1	9.7	3.0	1.2	402	402	15.2
EX-183	1	Gilding Metal	56.2	32.2	10.9	.7	681	681	16.7
	2	Gilding Metal	57.8	26.9	12.8	2.5	483	496	14.4
EX-182	1	Gilding Metal	40.6	24.5	31.9	3.0	470	615	15.3
	2	Gilding Metal	47.8	25.5	17.6	9.1	427	469	13.4
<u>Unplated Barrels</u>									
854342	1	Nylon Lot S2B	75.1	14.1	6.1	4.7	594	599	17.1
	2	Nylon Lot S9	67.0	9.5	9.5	14.0	399	407	16.6
856686	1	Gilding Metal	46.9	34.1	15.3	3.7	510	513	15.3
855119	1	Gilding Metal	76.2	15.7	7.2	.8	235	436	Not Taken

CONFIDENTIAL

Omitting from the count the first round of each burst after the third, one finds that the bursts in the first cycle which failed the yaw criterion were the third through the eighth, and the tenth. In the second cycle, the fifth, sixth, tenth, eleventh, and twelfth bursts failed the yaw criterion. The failure to pass the conventional yaw criterion was not taken very seriously, since there appeared to be no very definite trend toward deterioration of performance, successive bursts in the same cycle passing or failing in quite an arbitrary way. (This is not the case for barrels fired with gilding-metal bands, where shortly after the first burst to fail on yaw, the accuracy of the gun declines precipitously.) Furthermore, the negligible amount of wear of the gun indicated no reason to believe that the barrel performance should be deteriorating.

It was accordingly decided to continue testing this barrel, and two more cycles were fired. As shown in Figures 6 and 9, in the summary table above, and in Appendix F, the results of these two cycles were completely satisfactory. After 2464 rounds, the barrel showed practically no wear, the velocity drop was negligible, and the yaw performance was somewhat better than expected with gilding-metal bands.

In the fourth cycle of this barrel, the bands fired in the first, fourth, and eighth bursts were of a diameter reduced to 0"823. This experiment was made for two reasons: (1) work in other gun calibers had indicated a possible improvement in range accuracy by reduction of band diameter, and (2) investigations of artificial aging of nylon had disclosed the possibility that under prolonged storage under very humid and hot conditions, nylon bands at 0"828 diameter might increase in size just enough to be troublesome in seating in the chamber of the gun. The 0"823 diameter bands showed no detectable difference in performance.

One more plated barrel has been fired for one cycle with 0"828 nylon bands, and a third has been fired for one cycle with 0"823 nylon bands. Both, as the data in Figures 7 and 10, in the summary table, and in Appendix F show, gave excellent performance, similar to that shown in the third and fourth cycles of the first barrel. Two plated

CONFIDENTIAL

barrels have been fired to end of life with standard gilding-metal bands, for comparison. Both had a velocity life (to 200 ft/sec drop) of about 1000 rounds, and an accuracy life of about 1150 rounds (see Appendix F).

One unplated barrel has been fired to end of life with 0.828 diameter nylon bands, and two for comparison with standard gilding-metal bands. The results are given in detail in Appendix G, and are summarized as regards yaw and dispersion in the summary table above, and as regards velocity and barrel wear in Figures 8 and 11.

The unplated barrel with nylon bands began with excellent yaw performance, which declined suddenly on the last burst of the first cycle to an extent sufficient to fail the burst by the yaw criterion. This performance was checked by firing a second cycle, during which there was a rather similar decline at the eighth burst. The accuracy life of this barrel is therefore conservatively set at 550 rounds. The two comparison barrels indicated an end of velocity life at about 550 rounds, with the accuracy still acceptable.

Bore photographs of plated and unplated barrels having fired nylon or gilding-metal bands are shown in Figures 12 to 15, Appendix A. It is interesting to note in Figure 13, the photograph of the unplated barrel fired with nylon bands, the rather large wear of the driving edge producing a tapered top of the land. This type of wear does not produce very much effect on the star-gauge readings, but may well be expected to promote failure of the nylon band. The photograph of the plated barrel fired with nylon bands shows no such effect.

DISCUSSION

It is gratifying that the problem of obtaining acceptable performance of nylon bands in a very hot gun presented no more difficulty than it did. Apparently the poor heat conductivity of the nylon, and the short time it remains in the barrel, prevent any appreciable heat softening of the material except in the case of the first round in a burst, as mentioned above.

The phenomenal increase in life observed with nylon bands in plated barrels is in line with results in other calibers. As a general rule, in plated guns the chromium prolongs the life of the gun essentially by the number of rounds it manages to stay intact. After the plating is breached, which occurs in the region of the origin, the gun wears at the same rate as an unplated gun. A nylon band, being considerably softer than a metal band, inflicts much less damage on the chromium in the process of engraving, and the chromium thus lasts for a number of rounds at present indeterminately large.

The reasons for the occurrence of numerous yawed rounds in two rapid-fire cycles with nylon bands, and their absence in four other cycles, is not understood at present, and must be investigated further. There appears to be some chance that this phenomenon is connected with the action of the gun and feeder, and that nylon is more sensitive to variations in such action than is gilding metal. Variations in ballistic conditions or in quality of nylon do not seem capable of yielding an explanation. At any rate, since the phenomenon does not occur in the first 100 or 150 rounds fired in a cycle, it may be of little consequence in service.

That the increased long-range dispersion observed with nylon bands in slow fire in a Mann barrel is not of serious consequence is supported by a comparison of the short-range dispersion patterns in rapid-fire given by nylon and gilding-metal bands, which are considerably closer together.

A comparison of the pattern sizes shown by the two band materials, from the summary table, indicates no appreciable difference, except for the two cycles which had the numerous yawed rounds. Inspection of the detailed tables in the Appendices shows that even for these two cycles the pattern sizes for the first two or three bursts are close to those characteristic of gilding metal.

A report is in preparation dealing with accelerating aging tests, which bear on the problem of storage life of nylon bands, with some data on the effect of molding conditions on the quality of nylon.

CONCLUSIONS

The extreme temperature firing indicated that a band design and a method of molding have been achieved which produce a band that is retained in flight at all firing conditions.

The rapid-fire results showed that very satisfactory performance of the band is obtained even in a very hot gun. In chromium-plated barrels the nylon bands produce a spectacular increase in gun life. One barrel has been fired for over 2400 rounds on a severe schedule with practically no wear while a similar barrel fired on the same schedule with gilding-metal bands is worn out after 1000 rounds. Unplated barrels also show an increase in life with nylon bands, but not to a similar extent. No evidence of band loss in rapid-fire has been observed. Yaw performance in rapid-fire has been in some cases inferior to that observed with gilding-metal bands, but none of these cases having occurred at less than 150 rounds of burst firing, they are not considered to be of importance in service use. The short-range dispersion obtained in rapid-fire is generally comparable with that obtained with gilding-metal bands.

In accuracy firing (slow fire in a Mann barrel) acceptable dispersion at long range is obtained.

REFERENCES

- (a) BUORD Conf ltr NP9 Re3b:CFJ:mt Ser 63652 of 24 September 1953
- (b) NPG Conf Report No. 1099 of 28 February 1953
- (c) NPG Conf Report No. 845 of 3 September 1951

APPENDIX A




Figure 1

NP9-67011
~~CONFIDENTIAL~~

Typical 20mm Type 2 Mod 2 projectiles before firing. View on right has modified crimping groove.




Figure 2

NP9-67010
~~CONFIDENTIAL~~

Microflash photographs, 100 ft. from muzzle, of 20 mm projectiles. Top view shows band retained and lower view illustrates typical band loss if loss did occur.





Figure 3

NP9-67012

~~CONFIDENTIAL~~

20mm Type 2 Mod 2 Projectile assemblies after
subjection to normal loading cycle showing
ramming effect on standard crimp (left) and
on modified crimp (right).



NPS 67026

FIGURE 4

MODIFIED CRIMPING GROOVE
 FOR 20MM PROJECTILE TYPE 2 MOD 2

SCALE : 10 - 1
 4/20/53 LEM

DRAWING NO.
 APL - 452

NP9-67016
CONFIDENTIAL

FIGURE . 5





Figure 6

TEST OF 20MM CHROME PLATED BARRELS
MUZZLE VELOCITY vs NUMBER OF ROUNDS
 (AVERAGE BURST VELOCITIES)



NP9-67024

Figure 7

TEST OF 20MM UNPLATED SHELLS
 MUZZLE VELOCITY VS NUMBER OF ROUNDS
 (AVERAGE BURST VELOCITIES)

3400

3200

3000

Velocity (F/S)

Number of Rounds	1500	2000
3000	0	0
2800	0	0
2600	0	0
2400	0	0
2200	0	0
2000	0	0
1800	0	0
1600	0	0
1400	0	0
1200	0	0
1000	0	0
800	0	0
600	0	0
400	0	0
200	0	0
0	0	0

PROJECTILE TYPE
 BARREL NO. 854342 T2-2 (Nylen Band)
 NO. 856686 M11-O (Gilding Metal Band)
 NO. 855119 M11-O (Gilding Metal Band)
 End of Erosion Schedule




Figure 9




Figure 10




Figure 11

NP9-67027
CRL

Distance from Breech
4":7 Origin of Bore
5":0
6":0
7":0
7":5

23":9
Gas Port

Figure 12

Bore Photograph of Chrome Plated 20mm Gun
Barrel No. FX 184 after firing 2464 rounds
of Type 2 Mod 2 (nylon banded) projectiles.





Figure 13
Gas Port



Origin
of Bore
4.7 in

NP9-67029
C-1L

Bore Photograph of Unplated 20mm
Gun Barrel No. 854342 after firing
1041 rounds of Type 2 Mod 2 (nylon
banded) projectiles.

Figure 14

23":9
Gas Port

7":5
7":0

6":0

4":7
Origin
of
Bore

Distance from Breech

NP9-67028
CONFIDENTIAL

Bore Photograph of Chrome Plated 20mm
Gun Barrel No. FX 183 after firing
1177 rounds of Mk II Mod O (gilding
metal bands) projectiles.

23":9
Gas Port

7":5

7":0

6":0

4":7
Origin
of Bore

5":0

5":5

Distance from Breech

NP9-67030
~~Compt-AJ~~
Bore Photograph of Unplated 20mm Gun
Barrel No. 856686 after firing 518 rounds
of Mk 11 Mod 0 (gilding metal bands)
projectiles.

Figure 15

APPENDIX B

TABLE 1
COMPLETE BEFORE AND AFTER FIRING DATA

Recovery Test of 20mm Mk 11 (Target) Projectiles with Nylon Bands fired in Mk 11 Mod. 2 Barrel No. 854063

Proj. No.	Firing Order 1/3C/53	Lot No.	Firing Temp. (°F)	Pounder Charge (grs.) IMR 6962	Muzzle Velocity (ft./sec.)	% Nominal Spin	Average Band Hardness R _{Br}		Band Diameter O.D. (ins.)		° Taw			
							After		Conditi- oning at +160°F		95°			
							Before Conditioning	Conditi- oning at +160°F	Before Conditioning	Conditi- oning at +160°F	From Muzzle	From Muzzle		
2C56	1	.4A	-65	685	3251	104.73	103	107	.8278	.8285	5	2-1/2	3	100
2057	2	.4A	-65	685	3251	104.73	104	108	.8276	.8285	0	0	0	100
2058	3	.4A	-65	685	3262	105.34	103	107	.8276	.8282	0	4	4	90
2059	4	.4A	-65	685	3252	105.34	102	108	.8275	.8288	4	0	0	100
2060	5	.4A	-65	685	3249	106.57	103	107	.8275	.8287	3	3-1/2	2-1/2	100
2061	6	.4A	-65	685	3238	--	105	107	.8275	.8285	3	3	2-1/2	100
2062	7	.4A	-65	685	3292	--	102	106	.8275	.8283	0	0	0	100
2063	8	.4A	-65	685	3212	--	103	108	.8276	.8286	0	0	0	100
2064	9	.4A	-65	685	3249	--	102	108	.8275	.8286	0	0	0	100
2065	10	.4A	-65	685	3232	--	102	106	.8275	.8287	0	0	0	100
2C66	11	.4B	-65	685	3243	105.01	102	108	.8272	.8280	0	0	0	100
2067	12	.4B	-65	685	3238	104.70	102	104	.8271	.8282	0	0	0	100
2068	13	.4B	-65	685	3290	104.75	102	106	.8277	.8286	4	4	2-1/2	Missed Picture
2069	14	.4B	-65	685	3232	104.76	102	108	.8279	.8288	4	4	2-1/2	100
2070	15	.4B	-65	685	3246	104.97	104	107	.8273	.8283	0	0	0	100
2071	16	.4B	-65	685	3246	--	102	108	.8279	.8290	3	2-1/2	0	100
2072	17	.4B	-65	685	3298	--	102	108	.8272	.8280	5	5	4	Missed Picture
2073	18	.4B	-65	.685	3240	--	103	107	.8273	.8281	0	0	0	100
2074	19	.4B	-65	685	3226	--	103	107	.8278	.8287	0	0	0	100
2075	20	.4B	-65	685	3238	--	103	107	.8279	.8290	2-1/2	2	2	100

Lot 4A Projectiles Type 2 Mod 2 according to APL 355B (Temp.: Mold +190°F, Proj. +160°F).

Lot 4B Projectiles Type 2 Mod 2 according to APL 355B (Temp.: Mold +60°F, Proj. +75°F).

Both lots of projectiles in temperature control at +160°F for 7 days, ambient 24 hours, and -65°F for a minimum of 4 hours. Approximately 30-45 seconds time out of cold box before firing.

TABLE 2
COMPLETE BEFORE AND AFTER FIRING DATA

Recovery Test of 20mm Mk 11 (Target) Projectiles with Nylon Bands in Mk 11 Mod 2 Barrel No. 854063

Proj. No.	Firing Order No.	Lot No.	Firing Temp. (°F.)	Powder Charge (grs.)	Muzzle Velocity (ft./sec.)	% Nominal Spin	Average Band Hardness $\frac{H_r}{R}$			Band Diameter O.D. (ins.)	° Yaw
							Before Conditioning	Before Test	After Conditioning		
2095	1	4A	-65	685	3334	98.43	102	--	.8277	.8277	4
2096	3	4A	-65	685	3369	98.52	102	105	.8277	.8277	0
2097	5	4A	-65	685	3361	98.72	105	--	.8277	.8277	0
2098	7	4A	-65	685	3364	99.02	103	--	.8277	.8277	2-1/2
2099	9	4A	-65	685	3358	--	104	--	.8277	.8277	0
2100	11	4A	-65	685	3357	--	103	--	.8277	.8277	0
2101	13	4A	-65	685	3362	--	105	--	.8278	.8278	1
2102	15	4A	-65	685	3368	--	102	--	.8277	.8277	0
2103	17	4A	-65	685	3366	--	101	--	.8277	.8277	2-1/2
2104	19	4A	-65	685	3462	--	103	104	.8276	.8276	0
2105	2	4B	-65	685	3382	98.55	104	--	.8277	--	0
2106	4	4B	-65	685	3372	98.52	104	--	.8278	--	0
2107	6	4B	-65	685	3369	98.42	103	--	.8278	--	0
2108	8	4B	-65	685	3394	97.19	104	--	.8278	.8278	2-1/2
2109	10	4B	-65	685	3358	--	101	--	.8287	.8286	2
2110	12	4B	-65	685	3374	--	100	--	.8282	--	C
2111	14	4B	-65	685	3358	--	101	--	.8278	--	C
2112	16	4B	-65	685	3368	--	102	--	.8278	--	1
2113	18	4B	-65	685	3353	--	101	105	.8278	--	0
2114	20	4B	-65	685	3273	--	101	105	.8282	--	C

Lot 4A Projectiles Type 2 Mod 2 according to APL 3558 (Temp.: Mold +190°F, Proj. +160°F).
Lot 4B Projectiles Type 2 Mod 2 according to APL 355B (Temp.: Mold +60°F, Proj. +75°F).

Both lots of projectiles in temperature control at -65°F for 4 hours, +160°F for 4 hours, ambient temperature for 16 hours. This cycle was repeated for 7 days. The projectiles were again subjected to -65°F for 4 hours and fired at that temperature.

TABLE 3

Recovery Test of 20mm Mk 11 (Target) Projectiles with Nylon Bands Fired in Mk 11 Mod 2 Barrel No. 854063

Proj. No.	Firing Order No.	Lot No.	Firing Temp. (°F)	Powder Charge (grs.)	Velocity SPDN 10285 (ft./sec.)	% Nominal Spin	Average Band Hardness R _H		Band Diameter (ins.)		Difference of Diameters after Temp. (+160°F) Control	% New 130° From Muzzle	% Band on In Flight
							Before	After	Conditi-	Conditi-			
							Before	After	Conditioning (+160°F)	Conditioning (Ambient)			
2145	2	4A	+160	685	3388	96.8	102	89	.8277	.8314	+.0037	3	100
2146	4	4A	+160	685	3362	98.9	101	--	.8277	.8320	+.0043	0	100
2147	6	4A	+160	685	3367	98.5	102	86	.8277	.8316	+.0039	2	100
2148	8	4A	+160	685	3373	--	102	90	.8280	.8318	+.0038	5	100
2149	10	4A	+160	685	3321	--	102	--	.8277	.8310	+.0033	2-1/2	100
2150	12	4A	+160	685	3352	--	--	--	--	--	--	2-1/2	100
2151	14	4A	+160	685	3352	--	--	85	--	--	--	2-1/2	100
2152	1	4B	+160	685	3361	95.0	102	80	.8272	.8320	+.0048	6	100
2153	3	4B	+160	685	3362	98.6	93	--	.8278	.8316	+.0038	3	100
2154	5	4B	+160	685	3352	98.5	103	--	.8281	.8322	+.0041	2-1/2	100
2155	7	4B	+160	685	3367	--	102	--	.8277	.8320	+.0043	5	100
2156	9	4B	+160	685	3326	--	101	85	.8277	.8320	+.0043	2-1/2	100
2157	11	4B	+160	685	3356	--	102	88	--	--	--	2-1/2	100
2158	13	4B	+160	685	3352	--	102	--	--	--	--	3	100
2159	15	4B	+160	685	3359	--	101	--	--	--	--	5	100
2160	16	4B	+160	685	3351	--	102	--	--	--	--	3	100
2161	17	4B	+160	685	3354	--	102	--	--	--	0	2-1/2	100

Lot 4A Projectiles Type 2 Mod 2 according to APL 355B (Temp.: Mold +190°F, Proj. +160°F).

Lot 4B Projectiles Type 2 Mod 2 according to APL 355B (Temp.: Mold +60°F, Proj. +75°F).

Projectiles subjected to +160°F temperature and 100% humidity for 7 days.

APPENDIX C

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

DESCRIPTION OF VELOCITY AND PRESSURE-TIME TEST

Ref: (c) NPG Conf Report No. 845 of 3 September 1951

1. Pressure-time curves were taken on rounds assembled with projectiles Type 2 Mod 2 (Nylon 0⁰3 band 0⁰828 diameter) and projectiles with Nylon 0⁰3 band 0⁰834 diameter (marked "SP"). Rounds assembled with projectiles Mk 11 Mod 0 were used for control.

2. All rounds were assembled as indicated in Table 4 from components on hand with the exception of the nylon projectiles. The nylon-banded projectiles were crimped in the case with the special crimp devised for these projectiles; the crimp for the gilding-metal-banded projectiles was standard. When fired, the projectile emergence was missed on the original projectiles with nylon rotating bands because the nylon was insulating the projectile from the barrel. Three more projectiles of each type were furnished and the muzzle exit recorded by the breaking of the muzzle wire. It will be noted that the rounds of one group of projectiles with nylon bands were fired alternately with those of the other group having nylon bands. Neither group was alternated with the group having copper bands. This was felt desirable to avoid any additional coppering of the barrel while these rounds were fired. All data were recorded by procedures covered in reference (c) except the projectile emergence times. All results are tabulated in Table 4. Typical pressure-time curves and a calibration are included as Figures 16 to 18 inclusive.

~~CONFIDENTIAL~~

TABLE 4
TABULATED VELOCITY AND PRESSURE-TIME DATA
Nylon and Gilding Metal Band Comparison
Piezo Gauge 13, Cell 4
Barrel No. 862897 Chemically Decoppered
672 Previous Rounds

Date 1953	Time	Rd.	Type	Weight (Grains)	Lot	Powder	Projectile			Crimp (Tons)	Times (ms) Ignition Exposure	Velocity (ft./sec.)	Piezo Pressure (psi)
							Type	Weight (Grains)	Crimp (Tons)			Muzzle Velocity (ft./sec.)	Muzzle Exit
10-23	1457	1	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	15	.53	2.02	*3268	*63,100	
10-23	1457	2	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	15	.53	2.02	*3266	*11,200	
10-23	1502	3	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1690.7	15	.51	3340	3340	
10-23	1506	4	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1688.8	15	2.04	3340	62,050	
10-23	1510	5	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1685.0	15	2.05	3338	59,900	
10-23	1513	6	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1685.9	15	.47	3338	10,900	
10-23	1516	7	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1687.1	15	.50	3338	11,400	
10-23	1519	8	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1679.4	15	.50	3337	59,500	
10-23	1523	9	IMR 6962	662	DSZA-8	Mr 11 Mod 0	Mr 11 Mod 0	1686.1	15	.47	3333	60,500	
			Averages					1686.1		.49	3342	10,975	
							T2-2 (Nylon Rotating Band 0°834 Dla.)				3346	59,450	
10-23	1527	10	IMR 7013	1A40302	620	T2-2 (Nylon Rotating Band 0°834 Dla.)	1607.6	20	.47			10,650	
10-23	1536	12	IMR 7013	1A40302	620		1606.5	20					
10-23	1557	14	IMR 7013	1A40302	620		1606.2	20	.50	1.99	3334	56,150	
10-23	1604	16	IMR 7013	1A40302	620		1606.0	20	.47		3292	54,050	
10-23	1612	18	IMR 7013	1A40302	620		1601.2	20	.49		3316	56,775	
10-23	1625	20	IMR 7013	1A40302	620		1610.0	20	.48		3331	57,000	
10-23	1637	22	IMR 7013	1A40302	620		1610.6	20	.50		3362	62,350	
			Averages					1606.9		.49	3327	10,875	
10-23	1532	11	IMR 7013	1A40302	620	T2-2 (Nylon Rotating Band)	1606.2	20	.42			55,600	
10-23	1555	13	IMR 7013	1A40302	620		1597.6	20	.47		3316	55,550	
10-23	1600	15	IMR 7013	1A40302	620		1605.8	20	.50		3305	55,500	
10-23	1608	17	IMR 7013	1A40302	620		1591.7	20	.48		3318	55,500	
10-23	1618	19	IMR 7013	1A40302	620		1611.0	20	.49		3329	57,850	
10-23	1631	21	IMR 7013	1A40302	620		1604.0	20	.44		3322	56,550	
10-23	1643	23	IMR 7013	1A40302	620		1602.5	20	.51		3344	59,600	
			Averages					1602.7		.47	3322	56,600	


* Not included in average.


TABLE 4 (Continued)

Barrel No. 862904 Chemically Decoppered
717 Previous Rounds

Date 1953	Time Std.	Powder			Projectiles			Crimp (Tons)	Times (ms) Ignition Emergence	Muzzle Velocity (ft./sec.)	(psi)	Piezo Pressure (psi)
		Type	Lot	Weight (Grains)	Type	Weight (Grains)						
11-24	1321	1	IMR 6962	DSZA-8	662	Mk 11 Mod 0	15	Warm-up	Warm-up	62,500	1,500	
11-24	1333	2	IMR 6962	DSZA-8	662	Mk 11 Mod 0	15	Warm-up	Warm-up	61,000	10,000	
11-24	1345	3	IMR 6962	DSZA-8	662	Mk 11 Mod 0	15	Warm-up	Warm-up	58,750	9,900	
11-24	1352	4	IMR 7C13	LA40302	620	T2-2 (Nylon Rotating Band 0#834 Dia.)	20	.45	.41	3320	3329	
11-24	1412	6	IMR 7013	LA40302	620	Rotating Band 0#834 Dia.	20	.21	2.21	3321	3329	
11-25	1342	7	IMR 7013	LA4C302	620					60,750	9,800	
		Averages			1599.3		.43	2.21	3332			
11-24	1405	5	IMR 7013	LA4C302	620	T2-2 (Nylon Rotating Band)	1600.8	.40	2.11	3286	57,800	10,300
11-24	1420	7	IMR 7C13	LA40302	620		1598.3	.40	2.10	3270	56,200	10,475
11-25	1338	6	IMR 7013	LA40302	620		1602.8	.20	2.22	3281	55,850	9,750
		Averages			1600.6		.40	2.14	3279			
11-25	1345	8	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1695.5	.45	2.17	3342	63,650	10,200
11-25	1354	9	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1700.2	.45	2.17	3336	63,350	10,200
11-25	1357	10	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1699.2	.49	2.15	3318	60,850	10,150
11-25	1400	11	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1696.0	.45	2.16	3325	62,200	10,350
11-25	1404	12	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1695.2	.45	2.16	3336	62,750	10,350
11-25	1407	13	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1697.5	.50	2.16	3338	62,900	10,650
11-25	1411	14	IMR 6962	DSZA-8	662	Mk 11 Mod 0	1702.5	.44	2.16	3314	61,250	10,500
		Averages			1698.0		.47	2.15	3330			

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339





PP9-64994
Typical piezo pressure record of 20mm round assembled with Type 2 Mod 2 Modified projectiles (barrel diameter 0.834). Time in 0.1 milliseconds.
Figure 17

CONFIDENTIAL
Type 2 Modified Projectiles

APPENDIX C




Figure 18

APPENDIX D

TABLE 5

ACCURACY TEST, 600 FOOT RANGE FIRED IN NEW ACCURACY BARREL

		7 August 1953						
Rd. No.	Projectile Type	Powder Charge IMR 7013 (Grains)	Corrected Muzzle Velocity (ft./sec.)	Yaw at 38 Feet (Degrees)	Width of Pattern (ins.)	Height of Pattern (ins.)	Distance from Center of Impact Area from Boresight (ins.)	Standard Deviation at 600 Feet (ins.)
		X	X	X	X	X	X	X
1	T2-2 (Nylon Rotating Band)	620	3297	3			+8.3	+2.7
2	(Standard Crimp)	620	3302	5			+2.1	-6.6
3		620	3266	2			-1.3	-4.7
4		620	3227	4			-8.4	-2.9
5		620	3220	2			+2.1	-5.2
6		620	3290	5			-6.5	+6.7
7		620	3331	5			+7.7	+5.3
8		620	3292	4			-8.2	-5.9
9		620	3299	4			-6.7	+3.3
10		620	3314	2			-1.8	-6.8
Average		3304		16.7	13.4		-3.3	-3.9
11		620	3220	4			-2.9	-3.8
12		620	3227	2			-2.9	+2.5
13		620	3316	5			+6.6	-1.4
14		620	3336	1			-4.4	+2.5
15		620	3336	2			-4.5	+1.9
16		620	3331	1			-6.6	+1.1
17		620	3318	1			-3.6	+3.1
18		620	3320	2			-3.3	+1.5
19		620	3340	3			-3.1	-4.7
20		620	3335	1			-2.9	+4.8
Average		3330		13.1	9.5		+0.4	-12.9
21		620	3375	1			-4.1	-4.5
22		620	3349	1			+1.0	-0.1
23		620	3355	2			-3.5	-2.7
24		620	3355	3			+3.9	-5.5
25		620	3342	3			+1.2	-3.3
26		620	3377	3			-5.4	-5.0
27		620	3336	3			-0.7	-9.2
28		620	3338	3			+3.4	+7.5
29		620	3353	2			-1.0	+6.0
30		620	3349	4			+5.4	+9.2
Average		3355		10.7	18.4		-1.9	-10.0
							3.34	6.03

TABLE 5 (Continued)

Rd. No.	Projectile Type	Powder Charge IMR 7013 (Grains)	Corrected Muzzle Velocity (ft./sec.)	Yaw at 38 Feet (Degrees)	Width of Pattern (ins.)	Height of Pattern (ins.)	Distance from Center of Impact Area from Boresight		Standard Deviation at 600 Feet (ins.)	
							X	Y	X	Y
31	T2-2 (Nylon Rotating Band)	620	---	2			+2.1	-1.4		
32	(Fired at -65° F) (Special Crimp)	620	3217	2			+5.8	-1.6		
33		620	--	3			+0.2	-4.1		
34		620	--	1			-4.1	-0.7		
35		620	--	2			-5.7	-1.8		
36		620	3163	3			-4.6	+4.5		
37		620	3161	2			-3.5	-2.0		
38		620	--	2			-4.1	-3.2		
39		620	--	2			-0.8	-4.5		
40		620	--	2			-2.5	-2.4		
Average			3180		11.5	9.0			-3.2	-9.1
41	T2-2 (Nylon Rotating Band) Or 834 Diameter (Special Crimp)	620	3279	3			-3.3	-5.9		
42		620	--	3			+2.7	-3.5		
43		620	3264	1			+4.0	+3.8		
44		620	3264	2			+0.9	+2.5		
45		620	3295	2			-2.0	-1.3		
46		620	3270	1			+1.5	-1.4		
47		620	3275	3			+1.8	-2.7		
48		620	3275	1			-0.5	+0.7		
49		620	3286	3			-4.0	+6.9		
50		620	3288	3			-1.9	-4.8		
Average			3277		8.0	11.8			-6.9	-10.0
51	Reference Rounds, Mk 11	633	3373	3			+1.7	-0.8		
52	Mod C (Standard Crimp)	633	3351	3			-2.2	+0.5		
53		633	3377	3			-2.2	+0.7		
54		633	3344	4			+2.8	+0.3		
55		633	3362	2			-4.0	-2.5		
56		633	3366	3			-1.7	-1.5		
57		633	3353	2			-2.6	0.0		
58		633	3371	3			-2.4	+0.3		
59		633	3353	3			+0.7	-1.4		
60		633	3357	2			+4.0	+2.5		
Average			3361		8.0	5.1			-4.0	-9.5
									2.63	1.38

CONFIDENTIAL
11 March 1954

TABLE 6
ACCURACY TEST, 600 FOOT RANGE FIRED IN NEW ACCURACY BARREL

Rd. No.	Projectile Type	Powder Charge MR 7C13 (Grains)	Corrected Muzzle Velocity (ft./sec.)	Yaw at 38 Feet (Degrees)	Yaw at 600 Feet (Degrees)	Distance from Center of Impact Area from Boresight (ins.)		Total Group Dispersion at 600 Feet (ins.)	Standard Deviation at 600 Feet (ins.)
						X	Y		
1	Reference Rounds,	633	3324	1	0	-2.73	-0.60		
2	20mm Projectile	633	3299	0	0	+2.17	+0.47		
3	Mk 11 Mod 0	633	—	0	0	+1.33	-2.31		
4		633	3295	0	0	-3.84	-1.28		
5		633	3323	2	0	+3.32	+1.52		
6		633	3323	1	0	+3.84	+2.23		
7		633	3306	1	0	+1.58	+0.12		
8		633	3286	1	0	-0.16	-0.98		
9		633	3301	C	0	-0.65	+2.31		
10		633	3299	0	0	+0.78	+0.12		
Average		3306	0.6			+2.35	-2.28	7.68	4.62
11	T2-Mod 2 (Nylon Rotating Band)	620	3255	1	0	+1.30	+0.10		
12		620	3267	0	0	-1.88	+2.18		
13		620	3263	0	0	-1.32	-2.15		
14		620	3263	0	0	-3.86	-0.22		
15		620	3293	2	0	+3.86	-5.63		
16		620	3265	0	0	-2.12	+4.34		
17		620	3257	0	0	-3.50	+0.90		
18		620	3265	2	0	-3.75	+2.42		
19		620	3274	2	0	+1.33	+5.63		
20		620	3255	0	0	-3.00	+2.17		
Average		3266	0.7			+5.75	-0.63	11.26	7.72
21	T2-Mod 6 (Nylon Rotating Band)	620	3208	0	0	-1.23	-4.25		
22		620	3308	1	0	-6.42	-2.14		
23	0.784 Diameter	620	3299	2	0	+1.87	+7.95		
24	Aft of Band	620	3282	1	0	-3.67	-0.23		
25		620	3291	2	0	+6.62	+1.80		
26		620	3280	1	0	+8.73	-3.17		
27		620	3295	2	0	+4.40	-7.95		
28		620	3274	1	0	+1.22	+4.12		
29		620	3288	1	0	-8.73	-5.20		
30		620	3286	2	0	+2.02	+1.30		
Average		3291	1.3			+3.90	-3.75	17.46	15.90

ACCURACY TEST. 1500 YARD RANGE FIRED IN NEW ACCURACY BARRREL

TABLE 7 (Continued)

Ammunition Lot Number and/or Projectile Type	Date	Rd. No.	Type No.	Powder Charge	Air Temp.	Wind Direction	Wind Velocity	Hand Velocity	Gun Elevation	Armament	Muzzle Velocity	Instrumental Velocity	Distance Between Screens	Time of Flight	Hit Position	Standard Deviation at 1500 yards (feet)	
				[Grains]	[°F]	From Line of Fire	[Knots]	[Feet]	[Elevation]	[Feet]	[Feet]	[Feet]	[Feet]	[Secs.]	[Feet]	[Feet]	
T2-2 (Nylon) Rotating Band, 0.334 Dia- meter	8-26	1239	1	620	88 1/2	—	0	1021.2	83 1/2	57' 06"	30.030	50.025	3278	7.88	1605	5.09	
	8-26	1241	2	620	88 1/2	—	0	1021.2	84	57' 06"	3287	2.300	7.15	1608	7.62	5.33	
	8-26	1243	3	620	88 1/2	—	0	1021.2	84	57' 06"	3276	2.275	8.71	1604	9.16	2.87	
	8-26	1245	4	620	88 1/2	—	0	1021.2	84	57' 06"	3298	2.218	6.43	1604	7.52	—	
	8-26	1246	5	620	88 1/2	—	0	1021.2	84	57' 06"	3297	2.286	2.48	1607	13.57	9.56	
	8-26	1248	6	620	88 1/2	—	0	1021.2	84	57' 06"	3263	2.233	5.48	1607	7.86	7.29	
	8-26	1250	7	620	88 1/2	—	0	1021.2	84	57' 06"	3295	2.230	1.70	1605	10.04	10.75	
	8-26	1251	8	620	88 1/2	—	0	1021.2	84	57' 06"	3263	2.289	6.32	1602	8.22	5.90	
	8-26	1252	9	620	87 1/2	—	0	1021.2	84	57' 06"	3276	2.238	5.01	1605	6.83	9.94	
	8-26	1255	10	620	87	—	0	1020.3	84	57' 06"	3280	2.279	8.72	1605	4.08	6.96	
	8-26	1257	11	620	87	—	0	1021.2	84	57' 06"	3291	2.218	4.53	1605	7.96	8.64	
	8-26	1259	12	620	87 1/2	—	0	1020.3	84	57' 06"	3271	2.240	6.76	1604	5.25	11.42	
	8-26	1301	13	620	88	—	0	1021.2	84	57' 06"	3287	2.271	5.79	1600	14.59	—	
	8-26	1303	14	620	88	—	0	1021.2	85	57' 06"	3272	2.321	5.86	1602	5.95	10.22	
	8-26	1305	15	620	88	—	0	1021.2	85	57' 06"	3295	2.232	4.30	1594	9.49	7.49	
	8-26	1306	16	620	88	—	0	1021.2	85	57' 06"	3293	2.247	6.19	1610	6.43	7.94	
	8-26	1308	17	620	89	—	0	1021.2	85	57' 06"	3204	2.229	7.78	1595	3.96	12.04	
	8-26	1310	18	620	88 1/2	—	0	1021.2	85	57' 06"	3293	2.287	3.79	1602	10.01	8.01	
	8-26	1312	19	620	88	—	0	1021.2	85	57' 06"	3291	2.311	10.12	1595	5.13	7.50	
	8-26	1314	20	620	88 1/2	—	0	1021.2	85	57' 06"	3295	2.246	6.81	1606	6.00	7.47	
	8-26	1316	21	620	88 1/2	—	0	1021.2	85	57' 06"	3285	2.265	2.68	1605	9.95	13.18	
	8-26	1317	22	620	88 1/2	—	0	1021.2	85	57' 06"	3282	2.249	6.32	1600	10.07	—	
	8-26	1319	23	620	88 1/2	—	0	1021.2	85	57' 06"	3289	2.244	4.91	1600	8.00	7.96	
	8-26	1321	24	620	88	—	0	1021.2	85	57' 06"	3204	2.229	3.49	1597	8.70	12.96	
	8-26	1322	25	620	88	—	0	1021.2	85	57' 06"	3252	2.211	6.01	1604	6.09	9.04	
	8-26	1327	1	T2-2 (Nylon) Rotating Band, 0.334 Dia- meter	620	89	—	0	1020.8	87	56' 36"	30.030	50.025	3226	3.50	1602	8.27
	8-26	1402	2	620	88 1/2	—	0	1020.8	87	56' 36"	3278	2.227	8.06	1602	3.67	11.25	
	8-26	1404	3	620	89	—	0	1020.8	87	56' 36"	3246	2.180	6.18	1603	6.35	10.25	
	8-26	1406	4	620	89	—	0	1020.8	87	56' 36"	3255	2.190	7.81	1607	5.60	16.05	
	8-26	1409	5	620	89	—	0	1020.8	87	56' 36"	3246	4.04	1600	10.95	—	—	
	8-26	1411	6	620	89 1/2	—	0	1020.8	87	56' 36"	3293	2.222	5.80	1595	7.95	6.76	
	8-26	1414	7	620	89	—	0	1020.8	87	56' 36"	3292	2.244	3.86	1600	8.00	10.10	
	8-26	1418	8	620	89	—	0	1020.8	88	56' 36"	3295	2.224	1.85	1602	1.08	11.13	
	8-26	1420	9	620	89 1/2	—	0	1020.8	89	56' 36"	3242	3.07	1602	10.24	8.69	—	
	8-26	1422	10	620	90	—	0	1020.8	89	56' 36"	3239	2.169	9.19	1605	2.57	11.94	
	8-26	1425	11	620	90	—	0	1020.8	89	56' 36"	3231	2.151	3.74	1604	7.98	12.72	
	8-26	1428	12	620	90	—	0	1020.8	89	56' 36"	3226	2.189	7.63	1602	4.30	13.47	
	8-26	1430	13	620	90	—	0	1020.8	89	56' 36"	3248	2.160	8.96	1602	3.12	13.01	
	8-26	1435	14	620	90	—	0	1020.8	89	56' 36"	3260	5.54	1605	6.24	—	—	
	8-26	1437	15	620	90	—	0	1020.8	89	56' 36"	3228	2.194	10.62	1610	1.08	11.13	
	8-26	1439	16	620	91	—	0	1020.8	89	56' 36"	3242	2.172	6.05	1602	8.07	12.22	
	8-26	1452	17	620	91	—	0	1020.8	89	56' 36"	3246	2.169	9.16	1604	7.98	12.72	
	8-26	1454	18	620	91	—	0	1020.8	89	56' 36"	3255	2.150	4.95	1595	7.98	12.72	
	8-26	1455	19	620	90 1/2	—	0	1020.8	89	56' 36"	3255	2.151	8.45	1602	5.35	11.07	
	8-26	1510	20	620	90	—	0	1020.8	89	56' 36"	3248	—	2.04	1603	5.98	16.63	
	8-26	1514	21	620	90 1/2	—	0	1020.8	89	56' 36"	3248	2.174	6.64	1597	7.76	16.49	
	8-26	1517	22	620	90 1/2	—	0	1020.8	89	56' 36"	3239	2.205	7.89	1597	3.82	10.81	
	8-26	1521	23	620	90 1/2	—	0	1020.8	90	56' 36"	3274	2.245	6.05	1604	8.17	6.95	
	8-26	1528	24	620	90 1/2	—	0	1020.8	90	56' 36"	3269	2.137	9.13	1602	4.76	17.10	
	8-26	1531	25	620	90	—	0	1020.8	90	56' 36"	3246	2.158	2.06	1598	9.16	11.29	

APPENDIX E

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

DATA PERTAINING TO THE RAPID-FIRE GUN LIFE TESTS

Gun

The 20mm aircraft gun Mk 12 Mod 0 used in these tests, which fires at a rate of approximately 1000 rounds per minute, was mounted on a stationary mount for normal rapid-fire operation.

Barrel

The 20mm Mk 11 Mod 2 barrels fired in these tests were either chrome plated with O.W.O.O6 hard chrome, chamber and bore, or unplated. The rifling had uniform twist of 1 turn in 25.587 calibers, and a uniform depth of .015.

Round Assembly

The 20mm Mk 11 Mod 0 (Target) projectiles, both standard and modified (nylon band and extra crimping groove) were assembled in Mk 5 steel cases with Mk 47 primers (with one exception; the primer Mk 4 was used in Barrel No. 856686). The standard projectiles were rubber crimped at a pressure of 15 tsi and the modified projectiles at 20 tsi pressure. The nose plugs were standard pointed dummy nose plugs.

Powder

The propellant, IMR 7013 Lots CDZA-1 and CDZA-3 (the latter also designated as 1A-40302), was a 20mm NH production powder. The two lots were of the same series, having the same nominal composition and granulation and the same approximate flame temperature (2880°K).

Yaw

The projectile yaw in degrees was measured at 1000 inches from the gun by means of a traveling paper screen. Actual degrees of yaw for each round was determined by measuring the maximum diameter of the hole cut in this screen.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Dispersion

The dispersion was measured at 1092 inches from the gun by means of a stationary cardboard target, and is expressed in terms of the horizontal and vertical dimensions in inches of the rectangle on the target enclosing all the impacts in one burst (approximately 50 rounds).

Velocity

The velocity measurements were taken for each round by means of a Potter recording counter chronograph. The magnetizing coil was placed at the muzzle of the gun and the velocity measured by means of coils placed at 30 and 80 feet from the muzzle.

Barrel Inspection

The barrels were inspected by observing the rifling and chamber before and after each cycle was fired with a borescope. Photographs were taken at points of interest, before and after firing each cycle, of the barrels firing nylon bands and after each cycle of some of the barrels firing gilding metal bands. The barrels, rifling and chamber, were gauged before and after firing each cycle. Each diameter at a dimension from the gauging plane was gauged three times on three different sets of lands or grooves.

~~CONFIDENTIAL~~

APPENDIX F

TABLE 8

Date Fired: 21 May 1953
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 500056
 20mm Barrel Mk 11 Mod 2 Serial No. EX-184 Chrome Plated (No Previous Rounds)
 Projectiles: Type 2 Mod 2 (Nylon Bands Lot S2A)
 Propellant: 670 grains of IMR 7CL3, Lot 1A40302 Powder

<u>Burst</u>	<u>Time</u>	<u>Belted</u>	<u>Fired</u>	<u>Rds. on Barrel</u>	<u>Cyclic Rate</u> (rpm)	<u>Muzzle Velocity</u> (ft./sec.)	<u>Yaw (Degrees)*</u>	Dispersion			<u>100% Pattern (ins.)</u>		
								<u>0-5</u>	<u>6-10</u>	<u>11-15</u>	<u>Over 15</u>		
									<u>No. Rds.</u>	<u>No. Rds.</u>	<u>No. Rds.</u>	<u>X</u>	<u>Y</u>
1	1111	50	50	50	1041	3428±13	31	12	4	3	**(21.9	23.0	
2	1113	50	50	100	1037	3416±13	30	10	6	4			
3	1115	50	50	150	1034	3420±15	14	13	12	11			
4	1117	47	47	198	1030	3410±17	14	12	9	13	--	--	
5	1119	50	50	248	1029	3403±15	10	8	11	21	--	--	
6	1121	50	50	298	1028	3406±19	11	6	15	18	--	--	
7	1123	50	50	348	1021	3424±26	15	10	12	13	22.1	26.9	
8	1125	50	50	398	1010	3408±19	16	8	6	20	26.5	27.0	
9	1128	50	50	448	1014	3401±19	25	4	10	11	25.2	24.2	
10	1130	33	33	498	998	3398±26	21	4	10	15	21.2	26.1	
10	1132	50	50	548	1015	3419±20	33	5	3	8	25.9	24.6	
11	1134	50	50	598	1004	3407±20	23	5	11	11	**(26.1	27.3	

NOTES: Gun stoppage Bursts 4 and 10 due to feeder failure.

* Rounds omitted could not be measured.

** An average single-burst-pattern size was calculated statistically from the total pattern size.
 The statistical average for first three bursts - Horizontal 18.6, Vertical 19.5.
 The statistical average for last two bursts - Horizontal 23.4, Vertical 24.5.

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABULATED FIRING DATA
TABLE 2

Date Fired: 18 September 1953
20mm Aircraft Gun Mk 12 Mod C Serial No. 501151
20mm Barrel Mk 11 Mod 2 Serial No. EX-184 Chrome Plated (598 Previous Rounds)
Projectiles: Type 2 Mod 2 (Nylon Bands Lot S2B)
Propellant: 620 grains IMR 7013, Lot 1A-40302 Powder

Burst Time	Belted Rds.	Cyclic Rate (r.p.m.)	Average Velocity (ft./sec.)	Yaw (Degrees)			Dispersion			Remarks
				0-5 No. Rds.	6-10 No. Rds.	11-15 No. Rds.	16-35 (ins.) No. Rds.	100% Pattern X Y		
1	1427	50	46	644	967	3270±13	33	8	2	Slow feed.
2	1429	50	50	694	976	3253±10	36	3	16.8	17.1
3	1431	50	43	7	978	3256±14	19	11	7	Slow feed.
3	1432	50	7	744	--	3238±17	19	13	11	Slow feed.
4	1434	50	50	794	971	3249±15	15	8	13	23.0
5	1436	50	50	844	976	3249±15	15	8	14	23.8
6	1438	50	31	7	976	--	3241±18	16	10	Slow feed.
6	1439	19	7	893	--	3242±15	19	13	12	Slow feed.
6	1439	11	11	943	958	3248±17	22	11	6	Shorted primer.
7	1441	50	50	50	952	3241±17	19	13	6	20.6
8	1445	50	50	952	952	3248±17	22	7	4	21.3
8	1445	13	13	991	1041	3255±17	22	15	6	21.9
9	1446	50	50	952	1091	3252±15	16	8	15	19.7
10	1448	50	50	948	1143	3240±18	18	10	12	24.8
11	1450	53	52	1194	943	3245±20	24	5	8	23.1
12	1452	51	51	--	--	--	--	--	14	22.7

TABULATED FIRING DATA

Date Fired: 23 April 1954
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 500201
 20mm Barrel Mk 11 Mod 2 Serial No. EX-184 Chrome Plated (11% Previous Rounds)
 Projectiles: Type 2 Mod 2 (Nylon Bands Lot 59)
 Propellant: 620 grains IMR 7013, Lot 1A-40302 Powder

Burst	Time	Belted	Fired	Barrel	Rds.	Cyclic Rate (rds.)	Average Velocity (ft./sec.)	Yaw (Degrees)			Dispersion			<u>Remarks</u>
								0-5 Rds.	6-10 Rds.	11-15 Rds.	Over 15 Rds.	No. (ins.)	No. (ins.)	
1	1415	50	18	1227	1025	3276±12	49					11.5	16.4	
2	1417	31	1258	1016	3266±14							15.4	14.5	
3	1419	50	1308	1037	3236±15	32	9	8	1			12.1	15.9	Breech block out of battery.
4	1421	50	1358	1032	3230±14	28	19	3						
4	1423	50	34	1392	1023	3236±20								
4	1424	15	15	1407	1019	3241±17	46	1	1	1	1	19.0	17.4	
5	1426	50	50	1457	1014	3237±19	46	3	1			13.8	16.8	
6	1428	50	50	1507	1005	3235±17	38	11	1			21.1	16.6	
7	1430	50	50	1557	997	3239±19	41	5	3		**1	18.1	20.1	
8	1432	50	50	1607	987	3240±18	39	8	3			17.6	16.0	
9	1434	50	23	1657	977	3243±18	37	10	3			20.3	17.2	
10	1436	50	23	1680	985	3231±23								
10	1438	27	27	1707	965	3220±19	41	7	1	1	1	21.6	19.3	Belt separation.
11	1440	50	50	1757	960	3238±19	43	5	1			21.4	17.1	
12	1442	50	50	1807	960	3240±20	43	3	3	**1	17.0	23.1		
			*15	1822	977	3241±10								Cold velocity. Last 10 rounds of burst figured for average.

* Gun at Ambient Temperature.

** 1st round in burst.

TABLE 11

Date Fired: 16 July 1954
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 501152
 20mm Barrel Mk 11 Mod 2 Serial No. EI-184 Chrome Plated (1832 Previous Rounds)
 Projectiles: Type 2 Mod 2 (Nylon Bands, Lots S9, S10, and S10M)
 Propellant: 620 grains IMR 7013, Lot 1A-4C302 Powder

Burst	Time	Belted	Fired	Barrel	Rds. on Barrel	Cyclic Rate (rds. min.)	Average Velocity (ft./sec.)	Rotating Band Lot	Yaw (Degrees)*			Dispersion			
									0-5 Rds.	6-10 Rds.	11-15 Rds.	Over 15 Rds.	No. Rds.	100% Pattern (in.)	
1	0959	10	10	1842	1023(5 rds) (5 rds)	3228 ^{**} 8 3236 ^{**} 7	S10 S10M	10	2	1	11.1	14.2			
2	1023	50	50	1892	1049	3228 ^{**} 12	S10M	38	1		16.7	14.3			
3	1025	50	50	1942	1058	3222 ^{**} 16	S10	45	3		15.3	18.5			
4	1027	50	50	1992	1012	3237 ^{**} 13	S10	50	1		21.4	19.1	Rd. in chamber - bolt out of battery.		
5	1029	50	31	2042	1041	3209 ^{**} 20	S10M	48	1						
				2073	1025	3224 ^{**} 19									
5	1030	18	18	2091	1016	3219 ^{**} 18	S10	47	1	1	17.9	18.0	Rd. in chamber - bolt out of battery.		
6	1031	50	36	2127	1017	3220 ^{**} 14									
6	1034	13	13	2141	1000	3208 ^{**} 22	S10	45	1	3	19.8	17.3			
8	1036	50	37	2191	1003	3216 ^{**} 20	S10	44	3		23.1	20.0	Rd. in chamber - bolt out of battery.		
8	1037	12	12	2241	994	3207 ^{**} 18	S10M	45	2	1	23.3	18.3	Rd. in chamber - bolt out of battery.		
9	1039	38	38	2290	984	3223 ^{**} 17	S9	47	2	1	17.6	19.9			
10	1041	50	50	2340	980	3230 ^{**} 18	S10	45	1	1	21.4	19.8	Rd. in chamber - bolt out of battery.		
11	1043	50	40	2380	973	3233 ^{**} 13									
11	1056	9	9	2389	984	3217 ^{**} 15	S10	46	2	2	22.2	16.7			
12	1060	50	24	2413	965	3225 ^{**} 19									
12	1060	26	26	2439	965	3226 ^{**} 20	S10	47	3		23.1	20.2			
		*25	25	2464	984(10 rds) (10 rds) (5 rds)	3260 ^{**} 14 3251 ^{**} 16 3261 ^{**} 13	S9 S10M S10								

NOTE: Bands of Lot S10M were machined to 0.823 diameter, others as molded at 0.828.

* Rounds omitted could not be measured.

** Gun at Ambient Temperature.

TABLE 12
20mm Barrel Mk 11 Mod 2 Serial EX-184 Chrome Plated.

Distance from Breech Surface (Ins.)	Diameters (Ins.) Bore Of 1870-0002-0000											
	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.
4.75	.7875	.789	.791	.791	.788	.7885	.789	.792	.7875	.7895	.790	.7915
5.00	.787	.786	.787	.787	.783	.7855	.7865	.787	.7875	.7865	.7865	.7915
6.00	.787	.785	.7855	.7855	.785	.785	.7845	.7855	.785	.786	.786	.787
7.00	.7875	.7845	.7845	.7845	.787	.7845	.7845	.7845	.7875	.7845	.7845	.7845
8.00	.7875	.785	.785	.785	.787	.785	.7845	.785	.787	.7845	.785	.785
9.00	.7875	.785	.785	.785	.787	.7845	.7845	.785	.787	.7845	.7845	.785
10.00	.7875	.785	.785	.785	.787	.7845	.7845	.785	.787	.7845	.7845	.785
15.00	.787	.786	.7865	.7865	.7865	.7865	.7865	.7865	.787	.785	.785	.785
20.00	.787	.7865	.7865	.787	.7875	.7875	.787	.7875	.787	.787	.787	.787
25.00	.787	.787	.787	.787	.7875	.7875	.787	.7875	.787	.7875	.7875	.7875
30.00	.787	.787	.787	.787	.788	.788	.7875	.7885	.7885	.7885	.7885	.7885
35.00	.787	.787	.788	.788	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885
40.00	.7865	.7865	.7875	.7875	.788	.7885	.7865	.7875	.786	.7865	.7865	.7875
45.00	.787	.788	.789	.789	.7895	.7895	.788	.789	.787	.7875	.7875	.7875
46.00	.787	.788	.7885	.7885	.789	.789	.7875	.789	.787	.7875	.7885	.7885
47.00	.7865	.7875	.788	.7885	.7885	.7885	.7865	.7875	.7875	.7875	.7875	.788
48.00	.7865	.7865	.7875	.7875	.7885	.7885	.7865	.7875	.7875	.7875	.7875	.7885
49.00	.786	.786	.7875	.7875	.7885	.7885	.786	.7875	.7875	.7875	.7875	.789
50.00	.786	.786	.787	.787	.7885	.7885	.786	.787	.786	.7875	.7875	.7885
51.00	.786	.786	.7875	.7875	.788	.788	.7865	.787	.788	.7875	.7875	.788
52.00	.7855	.7855	.789	.789	.7905	.7905	.7855	.789	.7905	.7895	.7895	.791
52.25	.7855	.7895	.7895	.789	.791	.791	.7855	.7895	.791	.7895	.7895	.791
Grooves (In 1870-0104-0-000)												
4.75	.821	.817	.8175	.8175	.821	.817	.817	.8175	.8175	.822	.817	.817
5.00	.821	.818	.8165	.817	.817	.817	.817	.8175	.8175	.821	.8165	.817
6.00	.8205	.8175	.817	.817	.8205	.8175	.817	.817	.817	.8175	.8175	.817
7.00	.8205	.8175	.817	.817	.8205	.8175	.817	.817	.8205	.817	.817	.817
8.00	.8205	.818	.818	.817	.817	.8175	.8175	.817	.817	.8205	.817	.8165
9.00	.8205	.818	.818	.817	.817	.8175	.8175	.817	.817	.8205	.817	.8165
10.00	.8205	.818	.8175	.8175	.8205	.818	.818	.8175	.8175	.8205	.817	.817
15.00	.8205	.8185	.8175	.8185	.8205	.818	.8185	.8175	.8175	.8205	.818	.818
20.00	.8205	.8185	.818	.8185	.8205	.8185	.8185	.8175	.8185	.8205	.8185	.8185
25.00	.8205	.8185	.818	.819	.8205	.819	.818	.8185	.8185	.8205	.819	.8185
30.00	.8205	.819	.819	.8195	.8205	.8195	.8185	.8195	.8195	.8205	.8195	.8195
35.00	.8205	.8195	.8195	.8195	.8205	.8195	.8195	.8195	.8195	.8205	.8195	.8195
40.00	.820	.819	.8185	.819	.820	.819	.818	.8185	.8185	.820	.819	.8185
45.00	.821	.819	.8195	.8195	.821	.820	.8195	.820	.820	.821	.820	.820
50.00	.821	.8195	.8195	.8195	.821	.820	.8195	.820	.820	.821	.820	.820
51.00	.8195	.819	.8185	.8185	.821	.820	.8195	.820	.820	.821	.820	.820
52.00	.819	.819	.8195	.8195	.821	.820	.8195	.820	.820	.821	.820	.820
52.25	.8195	.819	.8185	.8185	.821	.820	.8195	.820	.820	.821	.820	.820

TABLE 13CHAMBER MEASUREMENT DATA

Barrel No. EX-184, 20mm Mk 11 Mod 2

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)			
		Prior to Firing	After Firing	After Rds.	After Firing Rds.
.359	1.1531+.002	1.1567	1.1570	1.1570	1.1570
1.209	1.1233+.002	1.1255	1.1256	1.1257	1.1258
1.739	1.1048+.002	1.1059	1.1060	1.1061	1.1062
2.239	1.0873+.002	1.0885	1.0887	1.0888	1.0888
2.739	1.0698+.002	1.0720	1.0722	1.0724	1.0724
3.039	1.0593+.002	1.0611	1.0613	1.0615	1.0615
Specs.	3.693+.005	.942	.9433	.9439	.9444
Actual	3.695	.942	.942	.9426	.9431
4.100	.834+.003	.847	.8468	.8472	.8472
4.200	.834+.003	.8437	.8428	.8422	.8421
4.300	.834+.003	.8431	.8414	.8410	.8403
4.330	.834+.003	.8439	.8413	.8415	.8411
4.370	.834+.003	.8448	.8426	.8428	.8416
4.380	.834+.003	.8448	.8423	.8428	.842
Specs.	4.458+.020	.828	.84C3	.8377	.8363
4.523		.828	.8236	.8237	.8237
4.563		.821	.8188	.8172	.8169

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABLE 14

TABULATED FIRING DATA

Date Fired: 29 May 1953
 20mm Aircraft Gun Mk 12 Mod C Serial No. 5C0056
 20mm Barrel Mk 11 Mod 2 Serial No. EX-183 Chrome Plated (No Previous Rounds)
 Ammunition: Production Lot ZS-68-HMC-53 - Standard 20mm Mk 11 Mod 0 Target Projectiles
 - 629 grains IMR 7013, Lot CDZA-1 Propellant Powder

Burst	Time	Belted	Fired	Rds.	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)			Dispersion			Remarks
							0-5		6-10	11-15		Over 15	
							No.	Rds.	No.	Rds.	No.	Rds.	
1	1118	50	50	974	3337±25	45	5	6	10.6	11.5	13.4	13.6	Stubbed round possibly due to defective end link.
2	1120	50	47	987	3362±24	41	6	1	21.0	15.6	10.6	11.5	
3	1122	50	50	147	985	3352±20	41	8	1	21.0	15.6		
4	1124	50	4	151	--	--	2	2					Failure to extract.
5	1126	45	4	155	--	--	3	1					Failure to extract.
6	1128	40	4	159	--	--	3	1					Failure to extract.
7	1130	35	35	194	983	*3346±23	30	5			15.5	14.4	
8	1132	50	50	244	981	3329±15	28	18	3	1	20.3	14.3	
9	1134	50	50	294	971	3314±18	22	24	2	2	16.1	18.5	
10	1136	50	50	344	961	3290±14	24	21	5		17.3	17.5	
11	1138	50	50	394	955	3247±12	18	25	7		15.8	13.8	
12	1140	50	50	444	947	3242±17	18	21	11		17.5	20.9	
13	1142	50	50	494	945	3224±14	26	15	9		18.1	16.9	
14	1144	49	49	543	938	3212±16	18	13	18		15.0	19.8	
15	1146	50	50	593	949	3210±17	18	24	7	1	21.1	16.3	
16	1148	50	34	627	938		16	13	5				Round in chamber but failed to fire.
17	1150	14	24	641	933	**3211±23	7	6	1	1	18.9	16.1	
18	1152	40	40	681	923	3209±23	23	11	5	1	13.50	17.4	

* Average of Bursts 4-7.
 ** Average of Bursts 16-17.

TABLE 15
TABULATED FIRING DATA

Date Fired: 24 September 1953
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 501151
 20mm Barrel Mk 11 Mod 2 Serial No. EX-183 Chrome Plated (681 Previous Rounds)
 Ammunition: Production Lot ZS-69-IMC-53 - Standard 20mm Mk 11 Mod 0 Target Projectiles
 - 629 Grains IMR 7013, Lot CDZA-1 Propellant Powder

Burst	Time	Belted	Fired	Rds. on Barrel	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)*			Dispersion Pattern (ins.)			Remarks
							0-5 Rds.	6-10 Rds.	11-15 Rds.	Over 15 Rds.	X	Y	
1	1255	50	50	731	1028	3180	50	50	9	1	9.6	9.8	
2	1257	50	49	780	1020	3167	39	9	1	1	11.7	14.4	Broken enc links.
3	1301	50	50	830	1019	3158	34	13	2	2	12.3	13.1	
4	1304	50	2	832	--	--							Slow feed.
4	1304	47	47	879	1010	3152	37	11	1	1	13.5	11.3	
5	1306	50	50	929	1005	Missed	22	19	8	8	15.6	15.2	
6	1307	50	50	979	989	3121	18	23	9	9	15.3	19.5	
7	1310	50	43	1022									Slow feed.
7	1310	7	7	1029	995	3101	21	10	9	9	16.3	14.0	
8	1312	49	49	1078	986	3109	28	18	3	3	14.5	21.8	
9	1314	49	49	1127	982	3090	22	15	12	12	17.9	15.8	
10	1315	50	50	1177	972	3066	8	12	17	17	17.2	19.6	End link jammed on strimmer.

* Rounds omitted could not be measured.

TABLE 16

Date Fired: 29 May 1953
Barrel No. EX-183, 20mm Mk 11 Mod 2 (No Previous Rounds)

Distance from Breech Surface (ins.)	Bore (0"787+0".002-0".000)						Diameters (ins.)						Grooves (0"817+0".004-0".000)					
	After			Prior			After			Prior			After			Prior		
	Prior	Firing	Rds.	Prior	Firing	Rds.	Prior	Firing	Rds.	Prior	Firing	Rds.	Prior	Firing	Rds.	Prior	Firing	Rds.
4.69 Bore-4.63	0.788	0.7875	0.8295	0.788	0.820	0.820	0.820	0.820	0.820	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
5.0	0.787	0.787	0.809	0.7875	0.811	0.820	0.820	0.820	0.820	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
6.0	0.7875	0.787	0.794	0.7870	0.795	0.820	0.820	0.820	0.820	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
7.0	0.787	0.787	0.7965	0.7870	0.7925	0.7925	0.7925	0.7925	0.7925	0.817	0.817	0.817	0.817	0.817	0.817	0.817	0.817	0.817
8.0	0.787	0.793	0.787	0.787	0.7925	0.7925	0.7925	0.7925	0.7925	0.820	0.820	0.820	0.820	0.820	0.820	0.820	0.820	0.820
9.0	0.787	0.792	0.787	0.792	0.792	0.792	0.792	0.792	0.792	0.8175	0.8175	0.8175	0.8175	0.8175	0.8175	0.8175	0.8175	0.8175
10.0	0.7875	0.791	0.7875	0.7905	0.7905	0.7915	0.7915	0.7915	0.7915	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
15.0	0.787	0.7855	0.787	0.7855	0.7855	0.7855	0.7855	0.7855	0.7855	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
20.0	0.787	0.7865	0.787	0.7865	0.7865	0.7865	0.7865	0.7865	0.7865	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
25.0	0.787	0.7885	0.7865	0.7885	0.787	0.787	0.787	0.787	0.787	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
30.0	0.7865	0.788	0.787	0.7885	0.7865	0.7865	0.7865	0.7865	0.7865	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
35.0	0.7865	0.7885	0.7865	0.7888	0.7865	0.7865	0.7865	0.7865	0.7865	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
40.0	0.786	0.788	0.7865	0.788	0.7865	0.786	0.786	0.786	0.786	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
45.0	0.786	0.789	0.7865	0.7885	0.786	0.786	0.786	0.786	0.786	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195	0.8195
46.0	0.786	0.789	0.786	0.789	0.786	0.786	0.786	0.786	0.786	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
47.0	0.786	0.789	0.786	0.7885	0.786	0.7885	0.786	0.7885	0.786	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
48.0	0.7855	0.789	0.7855	0.789	0.7855	0.7855	0.7855	0.7855	0.7855	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
49.0	0.7855	0.789	0.7855	0.789	0.7855	0.789	0.7855	0.789	0.789	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
50.0	0.7855	0.7885	0.7855	0.7885	0.7855	0.7885	0.7855	0.7885	0.7855	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
51.0	0.7855	0.7885	0.7855	0.788	0.7855	0.788	0.7855	0.7875	0.7855	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
52.0	0.786	0.7895	0.7855	0.7895	0.7895	0.7895	0.7895	0.7895	0.7895	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185	0.8185
52.25	0.786	0.7895	0.786	0.7895	0.786	0.7895	0.786	0.7895	0.786	--	--	--	--	--	--	--	--	--
52.40	--	--	--	--	--	--	--	--	--	0.820	0.8205	0.820	0.820	0.820	0.820	0.820	0.820	0.820

TABLE 16 (Continued)

Barrel No. EX-183, 20mm Mk 11 Mod 2 (681 Previous Rounds)

Distance from Breech Surface (ins.)	Bore (0 ⁰ :787+0 ⁰ :002-0 ⁰ :000)						Diameters (ins.)						Grooves (0 ⁰ :817+0 ⁰ :004-0 ⁰ :000)					
	After			After			After			Prior			After			After		
	Prior	Firing	Prior	Firing	Prior	Firing	Firing	Rds.	Firing	Rds.	Firing	Rds.	Firing	Rds.	Firing	Rds.	Firing	Rds.
4.70																		
5.00																		
6.00																		
7.00																		
8.00	0.793		0.7925	0.803		0.7925					0.817		0.8170	0.815	0.817			
9.00	0.792		0.792	--	0.792	--					0.8175		0.8165	0.816	0.8175			
10.00	0.791	0.797	0.7915	0.796	0.7915	0.7965					0.8165		0.8165	0.818	0.8165			
15.00	0.7855	0.790	0.7855	0.7915	0.7855	0.7905					0.8185		0.8175	0.8175	0.8175			
20.00	0.7865	0.787	0.786	0.788	0.786	0.7875					0.8185		0.8175	0.817	0.8185			
25.00	0.7885	0.787	0.787	0.7875	0.787	0.788					0.8185		0.8180	0.8175	0.8185			
30.00	0.788	0.7885	0.787	0.788	0.787	0.788					0.8185		0.8185	0.818	0.8185			
35.00	0.7885	0.789	0.7875	0.789	0.7875	0.7885					0.8185		0.8185	0.818	0.8185			
40.00	0.788	0.789	0.7875	0.789	0.7875	0.7885					0.8185		0.8185	0.818	0.8185			
45.00	0.789	0.791	0.789	0.7905	0.789	0.789					0.819		0.8185	0.819	0.8185			
46.00	0.789	0.7905	0.7885	0.790	0.7885	0.790					0.819		0.8185	0.819	0.8185			
47.00	0.789	0.7905	0.7885	0.790	0.7885	0.790					0.8185		0.8185	0.818	0.8185			
48.00	0.789	0.790	0.7885	0.790	0.7885	0.7895					0.8185		0.8185	0.818	0.8185			
49.00	0.789	0.790	0.789	0.790	0.789	0.790					0.8185		0.8185	0.818	0.8185			
50.00	0.7885	0.790	0.788	0.7895	0.788	0.7895					0.8185		0.8185	0.818	0.8185			
51.00	0.7885	0.7895	0.7875	0.789	0.7875	0.789					0.8185		0.818	0.8185	0.818			
52.00	0.7895	0.791	0.7895	0.791	0.7895	0.791					0.819		0.819	0.819	0.8195			
52.25	0.7895	0.791	0.7895	0.791	0.7895	0.791					0.8205		0.819	0.819	0.8205			

TABLE 17

Barrel No. EX-183, 20mm Mk 11 Mod 2

CHAMBER MEASUREMENT DATA

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)		
		Prior to <u>Firing</u>	After Firing Rds.	After Firing Rds.
.359	1.1531+.002	1.1548	1.1550	1.1551
1.209	1.1233+.002	1.1248	1.1255	1.1256
1.739	1.1048+.002	1.1044	1.1054	1.1055
2.239	1.0873+.002	1.0871	1.0882	1.0883
2.739	1.0698+.002	1.0708	1.0717	1.0719
3.039	1.0593+.002	1.0608	1.0616	1.0618
Specs.	.942	.9453	.9457	.9462
2.6975		.942	.9424	.9429
4.100	.834+.003	.8431	.8433	.8434
4.200	.834+.003	.8444	.8397	.8404
4.300	.834+.003	.8406	.8375	.8385
4.320	.834+.003	.8401	.8375	.8375
4.360	.834+.003	.8432	.8405	.8408
4.370	.834+.003	.8432	.8404	.8408
Specs.	.828	.8346	.8315	.8315
4.458+.020		.828	.8285	.8287
4.489		.821	.8327	.8358
4.530				

Note: Barrel Chamber Surface Finish Prior to Firing 6-21 Microinches.

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABLE 18

Date Fired: 3 February 1954
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 500C43
 20mm Barrel Mk 11 Mod 2 Serial No. EX-182 Chrome Plated (5 Previous Rounds)
 Ammunition: Production Lot ZS-69-HMC-53 - Standard 20mm Mk 11 Mod 0 Target Projectiles
 - 629 grains IMR 7C13, Lot CDZA-1 Propellant Powder

TABULATED FIRING DATA

<u>Burst</u>	<u>Time</u>	<u>Belted</u>	<u>Fired</u>	<u>Rds.</u> on <u>Barrel</u>	<u>Cyclic Rate (rpm)</u>	<u>Average Velocity (ft./sec.)</u>	Yaw Degrees)*			Dispersion 100% Pattern		
							<u>0-5 Rds.</u>	<u>6-10 Rds.</u>	<u>11-15 Rds.</u>	<u>Over No. No. Rds.</u>	<u>X (ins.)</u>	<u>Y</u>
1	0955	10	10	15	918	3332±36	10	9	2	9.9	8.1	
2	1038	50	50	65	985	3351±31	21	9	11	11.4	16.7	
3	1041	50	50	115	992	3387±24	14	9				
4	1043	50	50	165	996	3381±27	14	7	18	2	17.5	19.1
5	1045	50	50	215	983	3352±28	14	11	12	1	18.7	17.4
6	1047	50	50	265	1006	3356±19	18	7	13	2	12.7	14.3
7	1049	50	50	315	993	3327±15	22	9	6	2	15.7	15.4
8	1051	50	50	365	970	3269±12	19	13	13	1	17.2	13.0
9	1053	50	50	415	958	3236±15	18	11	16	1	18.9	15.4
10	1055	50	50	465	952	3218±18	13	13	20	1	13.9	16.8
11	1057	50	50	515	947	3225±16	11	14	19		15.6	14.8
12	1100	50	50	565	939	319C±21	13	7	10	2	16.2	17.4
13	1102	50	50	615	936	3177±22	4	5	10	2	16.4	14.3
		**10	10	625	931	3204±26						

* Rounds omitted could not be measured.

** Gun at Ambient Temperature.

NPG REPORT NO. 1342
 NAVORD REPORT NO. 1339

TABLE 12TABULATED FIRING DATA

Date Fired: 12 February 1954
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 500243
 20mm Barrel Mk 11 Mod 2 Serial No. EX-182 Chrome Plated (625 Previous Rounds)
 Ammunition: Production Lot ZS-69-HMC-53 - Standard 20mm Mk 11 Mod C Target Projectiles
 - 629 grains IMR 7C13, Lot CDZA-1 Propellant Powder

Burst	Time	Belted	Fired	Rds. on Barrel	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)*						100% Pattern X Y	
							0-5		6-10		11-15			
							No.	No.	No.	No.	No.	No.		
1	1107	10	10	635	918	3096±13	29	18	1	8	1	1	-- --	
2	1109	50	50	685	971	3106±17	21	15	1	1	1	1	9.5 10.7	
3	1111	50	50	735	970	3122±18	23	12	11	11	1	1	10.1 11.3	
4	1113	50	50	785	977	3139±21	23	12	11	11	1	1	13.5 11.7	
5	1115	50	29	814	965	3122±24	15	7	3	3	1	1	-- --	
6	1116	22	21	835	968	3104±21	12	6	2	2	1	1	10.6 13.7	
7	1118	50	50	885	957	3107±21	29	9	8	8	4	4	14.3 14.3	
8	1120	50	50	935	957	3090±23	18	8	8	11	7	7	18.4 16.6	
9	1122	50	50	985	952	3C90±20	17	11	11	13	9	9	14.6 14.6	
10	1124	50	49	1034	945	3C93±23	23	11	11	11	5	5	13.7 14.6	
11	1126	50	50	1084	936	3087±29	17	12	7	12	7	7	16.2 19.9	
		**10	10	1094	926	3099±15					13	13		

Notes: Gun stoppage on Burst 5 due to bolt stopping 1!5 out of battery.

* Rounds omitted could not be measured.
 ** Gun at Ambient Temperature.

NPG REPORT NO. 1342
 NAVORD REPORT NO. 1339

TABLE 20
Barrel No. EX-182, 20mm Mk 11 Mod 2

Distance from Breech Surface (ins.)	Bore (On 784 On 002-Off 000)										Diameters (ins.)										Grooves (On 817+Off 000)									
	Prior to Firing	After Firing	After Firing	Prior to Firing	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.								
	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.	Rds.		
4.69	.7875	Note 1	Note 1	.7880	Note 1	Note 1	.7885	Note 1	.7890	Note 1	.7885	.7880	.7875	Note 1	.7870	.7865	.7860	.7855	.7850	Note 1	.7855	.7850	.7845	.7840	.7835	.7830	.7825	.7820	.7815	.7810
5.00	.7870	Note 1	Note 1	.7875	Note 1	Note 1	.7880	Note 1	.7885	Note 1	.7885	.7880	.7875	Note 1	.7870	.7865	.7860	.7855	.7850	.7845	.7840	.7835	.7830	.7825	.7820	.7815	.7810	.7805	.7800	
6.00	.7870	.7960	Note 1	.7870	.7960	.7960	.7870	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	
7.00	.7870	.7960	.7960	.7870	.7960	.7960	.7870	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	.7960	
8.00	.7875	.7955	.7955	.7875	.7955	.7955	.7875	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	
9.00	.7870	.7950	.7950	.7870	.7950	.7950	.7870	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	.7950	
10.00	.7870	.7955	.7955	.7870	.7955	.7955	.7870	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	.7955	
15.00	.7870	.7860	.7860	.7875	.7860	.7860	.7870	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	.7860	
20.00	.7865	.7860	.7860	.7870	.7865	.7865	.7870	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	
25.00	.7865	.7865	.7865	.7870	.7865	.7865	.7870	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	
30.00	.7865	.7865	.7865	.7870	.7865	.7865	.7870	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	
35.00	.7865	.7860	.7860	.7870	.7865	.7865	.7870	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	.7865	
40.00	.7860	.7875	.7875	.7860	.7875	.7875	.7860	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	.7875	
45.00	.7865	.7885	.7885	.7865	.7885	.7885	.7865	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	
46.00	.7865	.7885	.7885	.7860	.7885	.7885	.7860	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	
47.00	.7860	.7880	.7880	.7860	.7880	.7880	.7860	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	
48.00	.7860	.7885	.7885	.7860	.7885	.7885	.7860	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	
49.00	.7860	.7885	.7885	.7860	.7885	.7885	.7860	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	
50.00	.7860	.7880	.7880	.7860	.7880	.7880	.7860	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	
51.00	.7860	.7880	.7880	.7860	.7880	.7880	.7860	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	.7880	
52.00	.7860	.7895	.7895	.7860	.7895	.7895	.7860	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	.7895	
52.25	.7860	.7900	.7900	.7860	.7900	.7900	.7860	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	.7900	
52.40	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	--	.7870	--	

Note 1: Unable to gauge lands - None at that point; worn off to "832 - "836 Dia. after 625 rds. and "836 - "841 Dia. after 1095 rds.

Note 2: Gauging Distance

4.63 Diameter from "834 to "835

4.69 Diameter from "832 to "836 (Origin of Bore)

5.00 Diameter from "819 to "835

4.63 Diameter from "8385 to "840

4.69 Diameter from "838 to "841 (Origin of Bore)

5.00 Diameter from "8315 to "835

6.00 Diameter from "811 to "824

TABLE 21

Barrel No. EX-182, 20mm Mk 11 Mod 2

CHAMBER MEASUREMENT DATA

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)		
		Prior to <u>Firing</u>	After Firing	After Firing Rds.
.359	1.1531+.002	1.1537	1.1540	1.1540
1.209	1.1233+.002	1.1233	1.1236	1.1237
1.739	1.1048+.002	1.1041	1.1046	1.1046
2.239	1.0873+.002	1.0865	1.0872	1.0872
2.739	1.0698+.002	1.0704	1.0710	1.0710
3.039	1.0593+.002	1.0598	1.0603	1.0604
Specs.	3.693±.005	.942	.9464	.9474
3.6991			.9420	.9426
4.100	.834*.003	.8414	.8413	.8413
4.200	.834+.003	.8411	.8402	.8404
4.300	.834+.003	.8409	.8379	.8382
4.320	.834+.003	.8399	.8364	.8373
4.330	.834+.003	.8399	.8369	.8377
4.370	.834+.003	.8420	.8381	.8391
4.380	.834+.003	.8420	.8381	.8391
Specs.	4.458+.020	.828	.8342	.8318
4.489			.8280	.8286
4.531			.8210	.8335

See Note 1

See Note 2
See Note 1
See Note 2

Note 1: Circumferential Tool Marks 3"!12 From Breech Face, Body of Chamber Pitted, Small Pitts in Shoulder and Neck Area.

Note 2: Some accumulation of Matter in Rifling, causing an irregular finish appearance, also some build up of substance in the Neck Area of Chamber having a Carbonized appearance. Small section of one land torn away approximately 23"!37 from breech face.

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABLE 22

Date Fired: 10 September 1954
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 506103
 20mm Barrel Mk 11 Mod 2 Serial No. 855108 Chrome Plated (5 Previous Rounds)
 Projectiles: Type 2 Mod 2 (Nylon Bands Lot S10M)
 Propellant: 630 grains IFR 7013, Lot 1A-4C302 Powder

Burst	Time	Belted	Fired	Barrel	Rds.	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)*			Dispersion 100% Pattern (ins.)			<u>Remarks</u>		
								9-5		6-10	11-15	Over 15	No. Rds.	No. Rds.		
								9-5	11-15	No. Rds.	No. Rds.	X	I			
1	1120	13	13	18	957	3323±10	984	3315±17	48	1	1	1	1	13.8	12.0	
2	1307	50	50	68	963	3321±13	13	16							12.6	14.2
3	1309	50	50	118	1007	3301±22	43	5	2						19.6	16.0
4	1311	50	50	168	1011	3298±22	41	4	4						20.1	13.6
5	1313	50	50	218	1011	3289±23	40	5	2						20.4	15.4
6	1315	50	50	268	997	3284±24	27	13	5						18.0	21.5
7	1317	50	50	318	995	3287±29	34	6	8						22.7	16.7
8	1319	50	50	368	996	3271±19	39	3	7						3	20.4
9	1321	50	50	418	991	3288±16	33	7	6						2	21.2
10	1323	50	50	468	976	3272±17	36	4	6						2	20.5
11	1325	50	50	518	960	3289±19	37	4	3						3	19.6
12	1327	50	50	568	956	3280±20	34	8	5						3	18.6
13	1329	**12	12	630	938	3318±9	12								3	22.3

* Rounds omitted could not be measured.
 ** Gun at Ambient Temperature.

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABLE 23

BARREL MEASUREMENT DATA

20mm Barrel Mk II Mod 2 Serial No. 855108 Chrome Plated

Distance from Breech Surface (ins.)	Bore (C:787+0.002-0.000)						Diameters (ins.)						Grooves (0.817+0.004-0.000)					
	After			After			After			After			After			After		
	Prior to Firing	Firing Rds.	Prior 630 to Firing	Firing Rds.	Prior to Firing	Firing Rds.	Prior to Firing	Firing Rds.	Prior to Firing	Firing Rds.								
4.75	.789	.7875	.789	.7875	.789	.789	.7875	.789	.7875	.789	.820	.8155	.820	.8155	.820	.8155	.820	.8155
5.00	.789	.7865	.789	.787	.789	.787	.786	.789	.786	.788	.820	.8155	.820	.816	.8205	.816	.816	.8205
6.00	.789	.7855	.789	.786	.789	.786	.7855	.789	.7855	.789	.820	.816	.820	.816	.820	.816	.816	.820
7.00	.789	.785	.789	.785	.789	.785	.785	.789	.785	.789	.820	.816	.820	.816	.820	.816	.816	.820
8.00	.7885	.7855	.7885	.785	.7885	.786	.7885	.786	.7885	.786	.820	.816	.820	.816	.820	.816	.816	.820
9.00	.7885	.786	.7885	.785	.7885	.785	.7885	.785	.7885	.785	.820	.816	.820	.816	.820	.816	.816	.820
10.00	.7885	.786	.7885	.785	.7885	.785	.7885	.785	.7885	.785	.820	.8165	.820	.817	.8205	.8165	.8165	.8205
15.00	.7885	.7865	.7885	.7865	.7885	.7865	.7885	.7865	.7885	.7865	.820	.817	.8205	.817	.8205	.817	.817	.8205
20.00	.7885	.787	.7885	.7865	.7885	.7865	.7885	.7865	.7885	.7865	.8205	.8175	.820	.818	.8205	.8185	.8185	.8205
25.00	.7885	.788	.7885	.7885	.7885	.788	.7885	.7885	.7885	.7885	.8205	.818	.8205	.8185	.8205	.819	.819	.8205
30.00	.7885	.788	.7885	.7885	.7885	.788	.7885	.7885	.7885	.7885	.8205	.8185	.821	.819	.8205	.8195	.8195	.8205
35.00	.789	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.7885	.821	.819	.821	.8195	.821	.8195	.821	.8195
40.00	.789	.789	.789	.7895	.789	.7895	.789	.7895	.789	.7895	.821	.8195	.821	.8195	.821	.8195	.821	.8195
45.00	.789	.7895	.789	.7895	.789	.790	.789	.790	.789	.790	.821	.8195	.821	.820	.821	.820	.820	.820
46.00	.789	.7895	.7895	.7895	.789	.7895	.7895	.789	.7895	.7895	.821	.8195	.821	.820	.821	.820	.820	.820
47.00	.789	.7895	.7895	.7895	.789	.7895	.7895	.789	.7895	.7895	.821	.820	.821	.820	.821	.820	.820	.820
48.00	.789	.790	.789	.790	.789	.790	.789	.790	.789	.790	.821	.820	.821	.820	.821	.820	.820	.820
49.00	.789	.790	.789	.790	.789	.790	.789	.790	.789	.790	.821	.820	.821	.820	.821	.820	.820	.820
50.00	.789	.7895	.7895	.7895	.789	.7895	.7895	.789	.7895	.7895	.821	.820	.821	.820	.821	.820	.820	.820
51.00	.789	.7895	.7895	.7895	.789	.7895	.7895	.789	.7895	.7895	.821	.820	.821	.820	.821	.820	.820	.820
52.00	.7895	.7895	.7895	.7895	.7915	.7895	.7895	.7915	.7895	.7915	.821	.8205	.821	.8205	.821	.8205	.821	.8205

TABLE 24

Barrel No. 855108, 20mm Mk 11 Mod 2

CHAMBER MEASUREMENT DATA

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)		After Firing 630 Rds.
		Prior to <u>Firing</u>	After Firing	
.359	1.1531+.002	1.1593	1.1595	
1.209	1.1233+.002	1.1287	1.1288	
1.739	1.1048+.002	1.1104	1.1105	
2.239	1.0873+.002	1.0928	1.0929	
2.734	1.0698+.002	1.0749	1.0750	
3.039	1.0593+.002	1.0643	1.0645	
Specs.	3.693+.005	.942	.9406	.9405
Actual	3.691		.942	.9418
4.100	.834+.003		.8364	.8361
4.200	.834+.003		.8364	.8361
4.300	.834+.003		.8364	.8334
4.400	.834+.003		.8315	.8313
Specs.	4.458+.020	.828	.828	.8262
Actual	4.4751			.8229

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Note: Post Firing Inspection: There is an irregular build up of matter on the rifling and in the neck area of chamber near the origin of rifling. The build up on the rifling is greater near the origin of rifling and gradually diminishes in quantity toward the muzzle.

~~CONFIDENTIAL~~

TABLE 25
TABULATED FIRING DATA

Date Fired: 4 June 1954

20mm Aircraft Gun Mk 12 Mod 0 Serial No. 5C0614
20mm Barrel Mk 11 Mod 2 Serial No. 854254 Chrome Plated (5 Previous Rounds)
Projectiles: Type 2 Mod 2 (Nylon Bands Lot S9)
Propellant: 62G grains IMR 7013, Lot 1A-40302 Powder

Burst	Time	Belted	Fired	Barrel	Rds.	Cyclic Rate on barrel	Average Velocity (ft./sec.)	Yaw (Degrees)			Dispersion			Remarks
								0-5		6-10	11-15		Over 15	
								No. Rds.	No. Rds.	No. Rds.	No. Rds.	No. Rds.	No. Rds.	
1	1333	15	15	20	1005	3249±15	15				8.2	9.0		
2	1341	50	50	70	1027	3271±13	50							Slow feeder.
3	1343	50	3	73		3246±18	3				15.6	11.6		Slow feeder.
4	1344	46	46	119	1023	3256±18	44	2						Failed to extract.
5	1346	50	2	121			2				13.7	10.1		Slow feeder.
6	1347	49	17	138	1005	3256±24	17							Failed to extract.
7	1349	31	29	167	1000	3254±15	28				13.3	13.9		Slow feeder.
8	1351	50	50	217	1004	3246±12	43	6	1					Slow feeder.
9	1353	50	15	232		3246±16	13	1	1					Slow feeder.
10	1355	33	33	265	992	3238±16	22	7	4		18.6	16.6		Failed to extract.
11	1357	50	9	274		3209±34	7	2						Ammunition chute broken.
12	1359	40	40	314	990	3251±16	36	2	1		1	14.7	18.6	Bolt out of battery.
13	1400	50	48	362	982	3248±13	34	9	4		1	19.6	19.0	Bolt out of battery.
14	1402	50	17	379		3237±14	13	3			1			Bolt out of battery.
15	1406	33	20	399		3235±14	12	7			1			Bolt out of battery.
16	1409	13	1	400										Bolt out of battery.
17	1410	12	3	403		321C±43	1							Gun failed to extract expended case. Also had a broken lock and bad extractor spring.
18*	1411	9	4	407		3221±37	3				1	17.6	16.1	

* The test was halted at this point because of the numerous gun stoppages.

TABLE 26

20mm Barrel Mk 11 Mod 2 Serial No. 854254 Chrome Plated

BARREL MEASUREMENT DATA

Distance from Breech Surface (ins.)	Bore (C"787+C"0C2-0"000)						Diameters (ins.)						Grooves (C"817+C"004-0"000)					
	Prior Firing Rds.	After Firing Rds.	Prior to 407 Firing Rds.	After Firing Rds.														
4.75	.790	.790	.790	.789	.7905	.790	.822	.819	.822	.819	.822	.819	.822	.819	.822	.819	.819	
5.00	.790	.7885	.790	.7885	.790	.7885	.822	.8195	.822	.819	.822	.819	.822	.819	.822	.819	.819	
6.00	.790	.788	.790	.7885	.790	.788	.822	.819	.822	.820	.822	.820	.822	.820	.822	.820	.820	
7.00	.790	.788	.790	.7885	.790	.788	.822	.819	.822	.8195	.822	.822	.822	.8195	.822	.822	.8195	
8.00	.790	.788	.790	.7885	.790	.788	.822	.819	.822	.8195	.822	.822	.822	.8195	.822	.822	.8195	
9.00	.7895	.788	.7895	.788	.7895	.788	.822	.8195	.822	.819	.822	.819	.822	.820	.822	.820	.820	
10.00	.7895	.788	.7895	.788	.7895	.789	.822	.820	.822	.8195	.822	.822	.822	.8195	.822	.822	.8195	
15.00	.789	.788	.789	.788	.789	.788	.8215	.819	.8215	.819	.8215	.819	.8215	.819	.8215	.819	.819	
20.00	.789	.788	.789	.788	.789	.788	.8215	.820	.8215	.820	.8215	.820	.8215	.820	.8215	.820	.820	
25.00	.7885	.788	.7885	.788	.7885	.788	.821	.820	.821	.820	.821	.820	.821	.820	.821	.820	.820	
30.00	.788	.788	.7885	.788	.7885	.788	.821	.820	.821	.820	.821	.820	.821	.820	.821	.820	.820	
35.00	.788	.788	.788	.788	.788	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.820	
40.00	.7875	.788	.7875	.788	.7875	.788	.8205	.819	.8205	.8195	.8205	.8195	.8205	.820	.8205	.820	.820	
45.00	.7875	.7885	.7875	.788	.7875	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	
46.00	.7875	.7885	.7875	.788	.7875	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	
47.00	.7875	.788	.7875	.788	.7875	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.820	
48.00	.7875	.788	.7875	.788	.7875	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.820	
49.00	.7875	.7875	.7875	.787	.7875	.787	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.820	
51.00	.7875	.788	.7875	.7875	.7875	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.820	
52.00	.7875	.7885	.7875	.788	.7875	.788	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.8205	.820	.820	

TABLE 27

Barrel No. 854254, 20mm Mk 11 Mod 2

CHAMBER MEASUREMENT DATA

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)		
		Prior to <u>Firing</u>	After Firing 4C7 Rds.	
.359	1.1531+.002	1.1588	1.1589	
1.269	1.1233+.002	1.1286	1.1286	
1.739	1.1048+.002	1.1096	1.1077	
2.239	1.0873+.002	1.0918	1.0919	
2.739	1.0698+.002	1.0744	1.0745	
3.039	1.0593+.002	1.0642	1.0642	
Specs.	3.693+.005	.9386	.9386	
Actual	3.6885	.942	.942	
4.100	.834+.003	.8385	.8384	
4.200	.834+.003	.8383	.8378	
4.300	.834+.003	.8383	.8364	
Specs.	4.458+.020	.8321	.8287	
Actual	4.4771	.828	.8236	

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Notes: R.M.S. value of chamber surface finish in microinches - chamber to front slope 8 to 21, chamber neck area 12-14. Front slope pitted, pits scattered around chamber body, non-concentric ring or raised surface around front slope chamber not within tolerances.

After firing there is a build up of matter on lands and grooves forming a rough crackle type finish similar to barrel EX-184. Fine heat cracks at origin of lands.

CONFIDENTIAL

APPENDIX G

TABLE 28

Date Fired: 11 September 1953
 20mm Aircraft Gun Mk 12 Mod C Serial No. 501151
 20mm Barrel Mk 11 Mod 2 Serial No. 854342 Unplated (5 Previous Rounds)
 Projectiles: Type 2 Mod 2 (Nylon Bands Lot S2B)
 Propellant: 62C grains IMR 7013, Lot 1A-40302 Powder

<u>Burst</u>	<u>Time</u>	<u>Belted</u>	<u>Fired</u>	<u>Rds. on Barrel</u>	<u>Cyclic Rate (rpm)</u>	<u>Average Velocity (ft./sec.)</u>	<u>Taw (Degrees)*</u>			Dispersion			
							<u>0-5</u>	<u>6-10</u>	<u>11-15</u>	<u>Over 15</u>	<u>No. Rds.</u>	<u>No. Rds.</u>	<u>No. Rds.</u>
<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>	<u>X</u>
1	1406	50	48	53	976	3336±13	42	6			11.5	8.5	Ammunition belt separation.
2	1408	50	50	103	996	3337±7	44	6	2	1	12.5	13.0	
3	1410	50	50	153	1021	3335±9	39	6		1	14.0	15.5	
4	1412	48	48	201	1C28	3323±16	38	7	2	1	16.0	15.0	
5	1414	50	50	251	1024	3318±9	39	7	3	1	18.0	20.5	
6	1416	50	50	301	1C10	3314±9	36	9	4	1	17.5	15.0	
7	1419	50	50	351	1C7	3318±9	39	9	1	1	17.0	16.5	
8	1421	50	50	401	1C1	3305±10	34	5	7	4	22.0	15.5	
9	1424	53	31	432	989	3290±10	16	5	7	2			Broken feeder anchor arms.
10	1429	22	22	454	991	3298±9	19	2		1	19.0	22.0	
11	1431	50	50	5C4	997	3295±10	3C	15	4	1	17.0	17.0	
12	1433	50	48	552	987	3282±14	42	3	2	1	19.5	20.5	Defective end link.
				6C4	991	3260±11	28	4	6	14	21.5	23.0	

* Rounds omitted could not be measured.

TABLE 29

TABULATED FIRING DATA

Date Fired: 20 May 1954
 20mm Aircraft Gun Mk 12 Mod 0 Serial No. 501614
 20mm Barrel Mk 11 Mod 2 Serial No. 854342 Unplated (6C4 Previous Rounds)
 Projectiles: Type 2 Mod 2 (Nylon Bands Lot S9)
 Propellant: 620 grains IMR 7013, Lot 1A-40302 Powder

Burst	Time	Belted	Fired	Barrel	Rds. on Rate (rpm)	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)*			Over No. No.	Dispersion 100% Pattern (Ins.)
								0-5	6-10	11-15		
								Rds.	Rds.	Rds.		
1	1420	15	15	619	1040	3233±8	15				11.0	7.8
2	1431	50	50	669	1059	3232±7	44	6			13.0	10.8
3	1433	50	50	719	1059	3227±12	42	6	2		13.1	13.1
4	1435	50	50	769	1057	3222±11	38	6	4	2	15.1	11.8
5	1442	50	50	819	1029	3219±13	41	4	4	1	12.6	12.4
6	1445	50	50	869	989	3210±14	41	3	3	3	18.9	19.3
7	1447	50	42	911	1013	3198±14	14	2	12	9	24.0	22.4
8	1449	50	50	961	991	3176±18	20	4	5	17	23.3	21.3
9	1451	50	50	1011	996	3158±20	12	7	8	24		
		**15	15	1026		3204±15						
21	May	**15	15	1041		3201±10	7	2	6			

* Rounds omitted could not be measured.

** Gun at Ambient Temperature.

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

CONFIDENTIAL

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABLE 30 BAFREL MEASUREMENT DATA

9mm Berretta M11 Mod 2 Serial No. 854342 Unplated

Distance from Muzzle Surface (In.)	Bore (0.7875-0.7900-0.7900)								Grooves (0.8175-0.8200-0.8200)							
	Diameters (In.)				After Firing				Prior to Firing				After Firing			
	Prior Firing to Muzzle Surface	After Firing Rds.	After Firing Rds.	After Firing Rds.	After Firing Rds.	After Firing Rds.	After Firing Rds.	After Firing Rds.								
0.00	.788	.789	.792	.7875	.789	.7915	.7885	.7875	.7885	.791	.818	.817	.817	.818	.815	.817
1.00	.788	.7885	.7915	.7885	.788	.7905	.788	.788	.788	.790	.818	.817	.818	.818	.817	.817
2.00	.788	.788	.791	.787	.788	.790	.7875	.7875	.788	.790	.818	.817	.817	.818	.817	.817
3.00	.788	.788	.7915	.7875	.788	.791	.788	.788	.788	.7915	.818	.817	.817	.817	.817	.817
4.00	.788	.7885	.792	.7885	.788	.792	.7875	.7875	.788	.792	.818	.817	.817	.817	.817	.817
8.00	.788	.7875	.788	.7875	.788	.7905	.7875	.7875	.788	.7905	.818	.817	.817	.818	.817	.817
12.00	.788	.7875	.790	.7875	.7875	.790	.7875	.7875	.7875	.790	.818	.817	.817	.818	.817	.817
16.00	.788	.788	.788	.7875	.7895	.7875	.7875	.7875	.7875	.7895	.818	.817	.817	.818	.817	.817
20.00	.788	.789	.787	.7875	.7895	.787	.7875	.7875	.7875	.7895	.818	.817	.817	.818	.817	.8165
22.00	.788	.787	.785	.7875	.7895	.787	.7875	.7875	.7875	.7895	.818	.817	.817	.818	.817	.8165
24.00	.788	.787	.785	.7875	.7885	.787	.7875	.7875	.7875	.7885	.818	.817	.817	.818	.817	.816
26.00	.788	.787	.785	.7875	.7885	.787	.7875	.7875	.7885	.789	.818	.817	.817	.818	.817	.815
28.00	.788	.787	.789	.788	.7885	.7865	.7885	.7885	.7885	.7885	.818	.8165	.8165	.818	.817	.816
30.00	.788	.7865	.788	.7865	.7885	.7865	.7865	.7865	.7865	.7889	.818	.817	.817	.818	.8165	.816
32.00	.788	.7865	.788	.7865	.7885	.7865	.7865	.7865	.7865	.7885	.818	.8165	.8165	.818	.8165	.8145
34.00	.788	.7865	.7885	.7865	.788	.787	.7865	.7865	.7865	.7885	.818	.816	.815	.816	.8145	.8145
36.00	.788	.7865	.7875	.7865	.7878	.788	.7865	.7865	.7865	.7885	.818	.816	.815	.816	.8145	.8145
38.00	.788	.7865	.7895	.7865	.788	.7878	.7865	.7865	.7865	.7887	.818	.815	.815	.816	.8145	.8145
40.00	.788	.787	.788	.787	.788	.787	.7875	.7875	.788	.7887	.818	.8155	.8135	.818	.8155	.8135
42.00	.788	.787	.7885	.788	.788	.787	.7885	.7885	.788	.7887	.818	.8155	.8145	.818	.8155	.8145
44.00	.788	.7875	.7895	.788	.788	.787	.7885	.7885	.788	.789	.818	.8155	.8135	.818	.8155	.8135
46.00	.788	.7885	.7905	.794	.7885	.7895	.794	.7885	.790	.790	.818	.815	.8135	.818	.815	.8135
47.00	.7885	.7935	.795	.7885	.793	.796	.7885	.7885	.793	.793	.818	.8155	.820	.818	.8165	.8165
47.50	.7885	.7985	.7985	.7985	.798	.795	.7985	.7985	.798	.798	.818	.817	.817	.818	.817	.817
		to								to						
47.75	.789	.8055	.789	.806	.789	.805	.8055	.8055	.8055	.805	.818	.815	.816	.818	.815	.816
47.81	.790	.8035	.8085	.790	.8035	.8035	.8035	.8035	.8035	.8035	.818	.815	.816	.818	.815	.816

TABLE 31

Barrel No. 854342, 20mm Mk 11 Mod 2

CHAMBER MEASUREMENT DATA

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameters (ins.)		
		Prior to <u>Firing</u>	After <u>Firing</u> 604 Rds.	After Firing 1041 Rds.
.359	1.1531+.002	1.1535	1.1536	1.537
1.209	1.1233+.002	1.1240	1.1241	1.1242
1.739	1.1048+.002	1.1053	1.1054	1.1056
2.239	1.0873+.002	1.0877	1.0879	1.0878
2.739	1.0698+.002	1.0703	1.0705	1.0706
3.039	1.0593+.002	1.0598	1.0600	1.0606
Specs.	3.693±.005	.942	.9418	.9427
Actual	3.698			
4.100	.834+.003	.8365	.8364	.8366
4.150	.834+.003	.8365	.8364	
4.200	.834+.003	.8364	.8351	.8355
4.250	.834+.003	.8364	.8353	
4.300	.834+.003	.8363	.8369	.8390
4.350	.834+.003	.8360	.8333	.8345
4.400	.834+.003	.8352	.8324	.8328
Specs.	4.458+.020	.828	.8293	.8319
4.478			.8252	.8305
4.500			.8209	.8236
4.515			.818C	.8264
				.8214

Note: Driving edge of lands noticeably worn after 1041 rounds for approximately 9" from origin, severe in intensity at origin and gradually diminishing toward muzzle, severe erosion at gas port, heat check marks in rifling varying from severe in intensity at approximately 2°C from origin and diminishing to mild intensity 16" from origin.

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABLE 32
TABULATED FIRING DATA

Date Fired: 9 November 1953
20mm Aircraft Gun Mk 12 Mod 0 Serial No. 500899
2Cmm Barrel Mk 11 Mod 2 Serial No. 856686 Unplated (5 Previous Rounds)
Ammunition: Local Assembly - Standard 20mm Mk 11 Mod 0 Target Projectiles
- 633 grains I.M.R. 7C13, Lot 1A-40302 Propellant Powder

Burst	Time	Belted	Fired	Barrel	Rds. on	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)*			Dispersion 100% Pattern (ins.)			Remarks
								0-5 No. Rds.	6-10 No. Rds.	11-15 No. Rds.	16-20 No. Rds.	X	Y	
1	1536	50	50	55	975	3331	32	--	--	--	7.9	9.6		
2	1530	51	51	106	960	3304	33	17	2	--	12.5	10.2		
3	1540	49	49	155	992	3299	28	19	2	--	15.8	10.0		
4	1542	50	39	194	950	3248	21	10	6	2	14.5	17.5		
4	1543	11	11	205	893	3238	21	5	4	--	14.7	16.3	Chamber empty.	
5	1545	50	50	255	976	3198	22	18	9	1	17.8	13.2		
6	1548	50	50	305	1019	3176	21	18	11	--	14.7	16.4		
7	1550	50	50	355	1004	3168	12	5	7	7	20.3	19.5	Defective Primer.	
8	1552	50	31	386	1001	3171	1	5	10	2	18.0	11.9		
8	1554	18	18	404	1002	3168	23	12	14	2	16.3	16.5		
9	1555	50	50	454	1008	3171	6	14	8	2	Broken feeder			
10	1557	50	30	484	986	3107	8	9	2	--	Broken anchor arm.			
10	1558	19	19	503	975	3122	10	4	1	--				
11	1600	50	15	518	--									

Test discontinued due to broken feed mechanism.

* Rounds omitted could not be measured.

TABLE 33

Barrel No. 856686, 20mm Mk 11 Mod 2 (5 Previous Rounds)

BARREL MEASUREMENT DATA

Distance from Breech Surface (ins.)	Bore (0"787+0"002-0"000)						Grooves (0"817+0"004-0"000)					
	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.	After Firing Rds.	Prior to Firing Rds.
4.75	0.790	0.8215	0.789	0.8215	0.789	0.8215	0.8195	0.8255	0.8195	0.8255	0.8195	0.8255
5.00	0.789	0.820	0.7885	0.820	0.788	0.820	0.8195	0.827	0.8195	0.8275	0.8195	0.827
6.00	0.788	0.814	0.788	0.814	0.788	0.814	0.8195	0.825	0.8195	0.8225	0.8195	0.8225
7.00	0.788	0.814	0.788	0.814	0.788	0.814	0.8195	0.820	0.8195	0.820	0.8195	0.820
8.00	0.788	0.8115	0.788	0.8115	0.788	0.8115	0.8195	0.8185	0.8195	0.8185	0.8195	0.8185
9.00	0.788	0.808	0.788	0.808	0.788	0.808	0.8195	0.8175	0.8195	0.8175	0.8195	0.8175
10.00	0.788	0.8045	0.788	0.8045	0.788	0.8045	0.8195	0.8175	0.8195	0.8175	0.8195	0.8175
15.00	0.788	0.799	0.788	0.799	0.788	0.799	0.8195	0.8175	0.8195	0.8175	0.8195	0.8175
20.00	0.7875	0.790	0.7875	0.790	0.7875	0.790	0.8195	0.8175	0.8195	0.8175	0.8195	0.8175
25.00	0.788	0.7875	0.7875	0.7885	0.7875	0.789	0.8195	0.8175	0.8195	0.818	0.8195	0.8175
30.00	0.788	0.788	0.7875	0.7875	0.7875	0.787	0.8195	0.8175	0.8195	0.8185	0.8195	0.8175
35.00	0.788	0.788	0.7875	0.7875	0.7880	0.7875	0.8195	0.8175	0.8195	0.8175	0.8195	0.8175
40.00	0.7875	0.788	0.7875	0.788	0.7875	0.788	0.819	0.8175	0.819	0.8175	0.819	0.8175
45.00	0.7875	0.789	0.7875	0.789	0.7875	0.790	0.819	0.818	0.819	0.8175	0.819	0.8175
46.00	0.7875	0.789	0.7875	0.789	0.7875	0.789	0.819	0.817	0.819	0.817	0.819	0.817
47.00	0.7875	0.789	0.7875	0.789	0.7875	0.789	0.819	0.817	0.819	0.817	0.819	0.817
48.00	0.7875	0.789	0.7875	0.789	0.7875	0.7895	0.819	0.817	0.819	0.817	0.819	0.817
49.00	0.7875	0.7895	0.7875	0.7895	0.7875	0.790	0.819	0.817	0.819	0.817	0.819	0.817
50.00	0.7875	0.790	0.7875	0.790	0.7875	0.790	0.819	0.817	0.819	0.817	0.819	0.817
51.00	0.7875	0.790	0.7875	0.791	0.7875	0.790	0.819	0.818	0.819	0.818	0.819	0.818
52.00	0.7875	0.7915	0.7875	0.793	0.7875	0.792	0.819	0.818	0.819	0.818	0.819	0.818

TABLE 24CHAMBER MEASUREMENT DATA

Barrel No. 856686, 20mm Mk 11 Mod 2

~~CONFIDENTIAL~~NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)		
		Prior to <u>Firing</u>	After Firing 518 Rds.	
.359	1.1531+.002	1.1558	1.1558	
1.209	1.1233+.002	1.1263	1.1263	
1.739	1.1048+.002	1.1072	1.1072	
2.239	1.0873+.002	1.0900	1.0901	
2.739	1.0698+.002	1.0727	1.0727	
3.039	1.0593+.002	1.0619	1.0619	
Specs.	.942	.9436	.9437	
3.693±.005				
4.100	.834+.003	.8401	.8401	
4.200	.834+.003	.8383	.8376	
4.300	.834+.003	.8371	.8368	
4.400	.834+.003	.8355	.8342	
Specs.	.828	.8316	.8324	
Actual	4.4755	.828	.8307	

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

TABULATED FIRING DATA

Date Fired: 12 May 1953
20mm Aircraft Gun Mk 12 Mod 0 Serial No. 5CC832
20mm Barrel Mk 11 Mod 2 Serial No. 855119 Unplated (56 Previous Rounds)
Ammunition: Production Lot ZS-7-HMC-53 - Standard 20mm Mk 11 Mod C Target Projectiles
- 661 grains IMR 6962 Lot DSZA-5 Propellant Powder

Burst	Time	Belted	Pired 'Barrel	Rds. on Rate (rpm)	Cyclic Rate (rpm)	Average Velocity (ft./sec.)	Yaw (Degrees)*			Remarks
							0-5 Rds.	6-10 Rds.	11-15 Rds.	
1	1050	50	6	62	974	3305	6			Round in chamber, firing pin mark.
2	1052	44	37	99	985	3361	36	1		Round in chamber, firing pin mark,
										hesitation in burst.
3	1055	50	44	143	1024	3315	34	6	3	Round in chamber, firing pin mark.
										Note: Above 3 stoppages due to defective synchronizing switch, new synchronizing switch installed.
4	1058	50	50	193	1008	3282	35	9	5	
5	1100	50	7	200	1000	3237	5	2	1	Stubbed round.
										Note: Feed mechanism EX-259 right hand removed and EX-214 right hand installed.
6	1102	42	42	242	995	3250	26	10	6	
7	1104	50	50	292	983	3222	37	9	3	
										Note: Paper in yaw machine broke, therefore, yaw not measured on remaining bursts.
8	1106	50	50	342	975	3210				
9	1108	50	50	392	972	3175				
10	1111	50	50	442	968	3163				
11	1115	50	50	492	955	3142				

* Rounds omitted could not be measured.

TABLE 36

BARREL MEASUREMENT DATA

20mm Barrel Mk 11 Mod 2 Serial No. 855119 (56 Previous Rounds)

Distance from Muzzle Surface (ins.)	Bore (C.M.787+0.002-0.000)						Grooves (0.817+0.004-0.000)						Diameters (ins.)					
	After			After			After			After			After			After		
	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	Prior to Firing	
4.75	0.7915	0.824	0.7915	0.824	0.7915	0.824	0.818	0.8255	0.818	0.818	0.8255	0.818	0.8255	0.818	0.8255	0.818	0.8255	
5.00	0.790	0.8195	0.7905	0.824	0.790	0.825	0.818	0.824	0.818	0.8255	0.818	0.8255	0.818	0.8255	0.818	0.8255	0.818	0.8255
6.00	0.7895	0.809	0.7895	0.824	0.789	0.824	0.818	0.819	0.818	0.819	0.818	0.819	0.818	0.819	0.818	0.819	0.818	0.819
7.00	0.789	0.805	0.789	0.824	0.789	0.824	0.818	0.8155	0.818	0.8155	0.818	0.8155	0.818	0.8155	0.818	0.8155	0.818	0.816
8.00	0.789	0.801	0.789	0.803	0.789	0.803	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.815
9.00	0.7885	0.789	0.7885	0.798	0.789	0.798	0.798	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.816	0.818	0.816
10.00	0.7885	0.7965	0.7885	0.796	0.789	0.796	0.818	0.816	0.818	0.816	0.816	0.818	0.816	0.816	0.816	0.816	0.816	0.8165
15.00	0.788	0.7915	0.788	0.792	0.788	0.7915	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165
20.00	0.7875	0.788	0.7875	0.7875	0.7875	0.7885	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8175
25.00	0.7875	0.787	0.787	0.787	0.787	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8175
30.00	0.7875	0.7875	0.787	0.787	0.787	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8175
35.00	0.787	0.7875	0.787	0.787	0.787	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.817
40.00	0.787	0.788	0.787	0.787	0.787	0.787	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.817
45.00	0.787	0.7875	0.787	0.787	0.787	0.787	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.817
46.00	0.787	0.787	0.787	0.787	0.787	0.787	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.817
47.00	0.787	0.7875	0.787	0.787	0.787	0.787	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.8165
48.00	0.787	0.7875	0.787	0.7875	0.787	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8175
49.00	0.787	0.788	0.788	0.787	0.788	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8175
50.00	0.787	0.7875	0.787	0.787	0.7875	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.817
51.00	0.787	0.788	0.788	0.787	0.788	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.817
52.00	0.787	0.789	0.788	0.788	0.788	0.787	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.8165	0.818	0.817
52.25	0.7875	0.788	0.787	0.787	0.787	0.787	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.816	0.818	0.8175
52.40	---	---	---	---	---	---	0.818	0.817	0.818	0.816	0.818	0.817	0.818	0.817	0.818	0.817	0.818	0.8175

TABLE 37

Barrel No. 855119, 2Cmm Mk 11 Mod 2

CHAMBER MEASUREMENT DATA

Distance from Breech Surface (ins.)	Drawing Dimensions	Chamber Diameter (ins.)	
		Prior to <u>Firing</u>	After Firing 492 Rds.
.359	1.1531+.002	1.1542	1.1542
1.209	1.1233+.002	1.1245	1.1245
1.739	1.1048+.002	1.1061	1.1059
2.239	1.0873+.002	1.0891	1.0891
2.739	1.0698+.002	1.0713	1.0713
3.039	1.0593+.002	1.0609	1.0609
Specs.	3.693±.005	•9391	•9389
4.100	•834+.003	•8348	•8348
4.200	•834+.003	•8347	•8340
4.300	•834+.003	•8347	•8324
Specs.	4.458+.020	•8293	•8303
4.464	•828	•828	•8298
4.512	•819	•819	•828

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

APPENDIX H

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

DISTRIBUTION

Bureau of Ordnance:

Ad3	1
Ad6	20
Re5	1
Re5e	1
Re3	1
Re3b	2

Armed Services Technical Information Agency
Document Service Center
Knott Building
Dayton 2, Ohio

5

Commanding General
Aberdeen Proving Ground
Aberdeen, Maryland
Attn: Technical Information Section
Development and Proof Services

1

Commander, Operational Development Force
U. S. Atlantic Fleet, U. S. Naval Base
Norfolk 11, Virginia

1

Watertown Arsenal
Watertown, Massachusetts

1

Frankford Arsenal
Philadelphia, Pennsylvania

1

Picatinny Arsenal
Dover, New Jersey

1

Superintendent
Naval Gun Factory
Washington 25, D. C.

1

Naval Ordnance Laboratory
White Oak, Maryland

1

~~CONFIDENTIAL~~

1

~~CONFIDENTIAL~~

NPG REPORT NO. 1342
NAVORD REPORT NO. 1339

DISTRIBUTION (Continued)

National Bureau of Standards	
Washington, D. C.	1
Chief of Naval Operations	5
Local:	
OTED	1
OTL	1
OT	1
OV	1
File	1

~~CONFIDENTIAL~~

<p>NPG 1342</p> <p>Naval Proving Ground, Oahlgren, Virginia</p> <p>DEVELOPMENT AND TEST OF NYLON ROTATING BAND FOR 20MM HIGH VELOCITY PROJECTILE, by R. B. Butler. 10 March 1955. 13p. tables. append A-H. NPG Report No. 1342. NAVORD Report No. 1339. Task assignment NPG-B-3b-225-1-54)</p> <p>Previously reported work on the development of a nylon rotating band for the 20mm aircraft gun Mk 12 had shown that the band as developed imparted full spin to the projectile, obfuscated satisfactorily, and did not fringe noticeably or produce unacceptable yaw, in slow fire at muzzle velocities up to 3500 ft/sec and at temperatures from -65° to 160°F. On the basis of a relatively small amount of firing, the band appeared to be completely retained in flight even at the temperature extremes. This report continues the account of the development work on this band, including additional extreme temperature firing, firing for ballistic accuracy, and rapid-fire tests.</p>	<p>I. Rotating bands - Test results</p> <p>I. Butler, R. B.</p> <p>II. NAVORD 1339</p> <p>CONFIDENTIAL</p> <p>Previously reported work on the development of a nylon rotating band for the 20mm aircraft gun Mk 12 had shown that the band as developed imparted full spin to the projectile, obfuscated satisfactorily, and did not fringe noticeably or produce unacceptable yaw, in slow fire at muzzle velocities up to 3500 ft/sec and at temperatures from -65° to 160°F. On the basis of a relatively small amount of firing, the band appeared to be completely retained in flight even at the temperature extremes. This report continues the account of the development work on this band, including additional extreme temperature firing, firing for ballistic accuracy, and rapid-fire tests.</p>
<p>NPG 1342</p> <p>Naval Proving Ground, Oahlgren, Virginia</p> <p>DEVELOPMENT AND TEST OF NYLON ROTATING BAND FOR 20MM HIGH VELOCITY PROJECTILE, by R. B. Butler. 10 March 1955. 13p. tables. append A-H. NPG Report No. 1342. NAVORD Report No. 1339. Task assignment NPG-B-3b-225-1-54)</p> <p>Previously reported work on the development of a nylon rotating band for the 20mm aircraft gun Mk 12 had shown that the band as developed imparted full spin to the projectile, obfuscated satisfactorily, and did not fringe noticeably or produce unacceptable yaw, in slow fire at muzzle velocities up to 3500 ft/sec and at temperatures from -65° to 160°F. On the basis of a relatively small amount of firing, the band appeared to be completely retained in flight even at the temperature extremes. This report continues the account of the development work on this band, including additional extreme temperature firing, firing for ballistic accuracy, and rapid-fire tests.</p>	<p>I. Rotating bands - Test results</p> <p>I. Butler, R. B.</p> <p>II. NAVORD 1339</p> <p>CONFIDENTIAL</p> <p>Previously reported work on the development of a nylon rotating band for the 20mm aircraft gun Mk 12 had shown that the band as developed imparted full spin to the projectile, obfuscated satisfactorily, and did not fringe noticeably or produce unacceptable yaw, in slow fire at muzzle velocities up to 3500 ft/sec and at temperatures from -65° to 160°F. On the basis of a relatively small amount of firing, the band appeared to be completely retained in flight even at the temperature extremes. This report continues the account of the development work on this band, including additional extreme temperature firing, firing for ballistic accuracy, and rapid-fire tests.</p>